



BRONMETAL

Copper Alloy CuA

Product format:

Sheet

Technical characteristics:

Copper alloy tolled plates

THICKNESS TOLERANCES IN HOT ROLLED PRODUCTS

Nominal thickness		Thickness tolerances for nominal widths						
Greater tan	Until included	Greater tan		Until included		Greater tan		Until included
		1)	2)	1)	2)	1)	2)	
-	2,5	In accordance		In accordance		In accordance		In accordance
2,5	5,0	± 0,25	± 0,30	± 0,30	± 0,35	± 0,35	± 0,45	
5,0	7,5	± 0,35	± 0,45	± 0,40	± 0,50	± 0,45	± 0,55	
7,5	10	± 0,45	± 0,60	± 0,50	± 0,65	± 0,55	± 0,75	
10	15	± 0,75	± 0,95	± 0,80	± 1,00	± 0,90	± 1,10	
15	25	± 0,95	± 1,20	± 1,05	± 1,30	± 1,30	± 1,60	
25	50	± 1,30	± 1,60	± 1,40	± 1,75	± 1,50	± 1,90	
50	-	± 1,50	± 1,90	± 1,65	± 2,05	± 1,80	± 2,20	
1) For all materiales, except CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R) 2) For all alloys CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R)								

THICKNESS TOLERANCES IN COLD ROLLED PRODUCTS

Nominal thickness		Thickness tolerances for nominal widths			
Greater than	Until included	to 350 inclusive	Greater than 350 to 700 inclusive	Greater than 700 to 1000 inclusive	Greater than 1000 to 1250 inclusive
0.1 ^b	0,2	± 0,018	-	-	-
0,2	0,3	± 0,022	± 0,03	± 0,04	-
0,3	0,4	± 0,025	± 0,04	± 0,05	± 0,07
0,4	0,5	± 0,03	± 0,05	± 0,06	± 0,08
0,5	0,8	± 0,04	± 0,06	± 0,07	± 0,09
0,8	1,2	± 0,05	± 0,07	± 0,09	± 0,10
1,2	1,8	± 0,06	± 0,08	± 0,10	± 0,11
1,8	2,5	± 0,07	± 0,09	± 0,11	± 0,13
2,5	3,2	± 0,08	± 0,10	± 0,13	± 0,17
3,2	4,0	± 0,10	± 0,12	± 0,15	± 0,20
4,0	5,0	± 0,12	± 0,14	± 0,17	± 0,23
5,0	6,0	± 0,14	± 0,16	± 0,20	± 0,26
6,0	7,0	± 0,16	± 0,19	± 0,23	± 0,29
7,0	8,0	± 0,18	± 0,22	± 0,26	± 0,32
8,0	9,0	± 0,20	± 0,25	± 0,29	± 0,35
9,0	10,0	± 0,22	± 0,28	± 0,32	± 0,38

^a For all alloys CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R), thickness tolerances must be multiplied by 1.25 and the result rounded to 0.01mm

^b included 0.1.

NOTE - For thicknesses above 10mm, tolerances are set forth in EN 1653