



BRONMETAL

Brass Zn

Product format:

Sheet

Technical characteristics:

Laminated for industrial applications

THICKNESS TOLERANCES IN HOT ROLLED PRODUCTS

Nominal thickness		Thickness tolerances for nominal widths						
Greater than	Until included	to 700 inclusive		greater 700 to 1000 inclusive		greater 1000 to 1500 inclusive		Greater than 1500
		1)	2)	1)	2)	1)	2)	
-	2,5	In accordance		In accordance		In accordance		In accordance
2,5	5,0	± 0,25	± 0,30	± 0,30	± 0,35	± 0,35	± 0,45	
5,0	7,5	± 0,35	± 0,45	± 0,40	± 0,50	± 0,45	± 0,55	
7,5	10	± 0,45	± 0,60	± 0,50	± 0,65	± 0,55	± 0,75	
10	15	± 0,75	± 0,95	± 0,80	± 1,00	± 0,90	± 1,10	
15	25	± 0,95	± 1,20	± 1,05	± 1,30	± 1,30	± 1,60	
25	50	± 1,30	± 1,60	± 1,40	± 1,75	± 1,50	± 1,90	
50	-	± 1,50	± 1,90	± 1,65	± 2,05	± 1,80	± 2,20	
<p>1) For all materials except, CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R).</p> <p>2) For all the alloys CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R).</p>								

THICKNESS TOLERANCES IN COLD ROLLED PRODUCTS

Nominal thickness		Thickness tolerances for nominal widths			
Greater than	Until included	to 350 inclusive	greater 350 to 700 inclusive	greater 700 to 1000 inclusive	greater 1000 to 1250 inclusive
0.1 ^b	0,2	± 0,018	-	-	-
0,2	0,3	± 0,022	± 0,03	± 0,04	-
0,3	0,4	± 0,025	± 0,04	± 0,05	± 0,07
0,4	0,5	± 0,03	± 0,05	± 0,06	± 0,08
0,5	0,8	± 0,04	± 0,06	± 0,07	± 0,09
0,8	1,2	± 0,05	± 0,07	± 0,09	± 0,10
1,2	1,8	± 0,06	± 0,08	± 0,10	± 0,11
1,8	2,5	± 0,07	± 0,09	± 0,11	± 0,13
2,5	3,2	± 0,08	± 0,10	± 0,13	± 0,17
3,2	4,0	± 0,10	± 0,12	± 0,15	± 0,20
4,0	5,0	± 0,12	± 0,14	± 0,17	± 0,23
5,0	6,0	± 0,14	± 0,16	± 0,20	± 0,26
6,0	7,0	± 0,16	± 0,19	± 0,23	± 0,29
7,0	8,0	± 0,18	± 0,22	± 0,26	± 0,32
8,0	9,0	± 0,20	± 0,25	± 0,29	± 0,35
9,0	10,0	± 0,22	± 0,28	± 0,32	± 0,38

^a For alloys CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R), thickness tolerances must be multiplied by 1.25 and the result rounded to 0.01mm

^b included 0.1.

NOTE - For thickness above 10mm, tolerances are set forth in EN 1653.