



BRONMETAL

BRASS

PRODUCT FORMAT: BAND

TECHNICAL CHARACTERISTICS: ROLLED COIL FOR INDUSTRIAL AND DECORATIVE

TOLERANCES ON THICKNESS OF HOT-ROLLED PRODUCTS

Nominal thickness		Thickness tolerances for nominal widths						
Greater than	Up to and including	Up to and including 700		Greater than 700, up to and inc. 1000		Greater than 1000, up to and inc. 1500		Greater than 1500
		1)	2)	1)	2)	1)	2)	
-	2,5	By agreement		By agreement		By agreement		By agreement
2,5	5,0	± 0,25	± 0,30	± 0,30	± 0,35	± 0,35	± 0,45	
5,0	7,5	± 0,35	± 0,45	± 0,40	± 0,50	± 0,45	± 0,55	
7,5	10	± 0,45	± 0,60	± 0,50	± 0,65	± 0,55	± 0,75	
10	15	± 0,75	± 0,95	± 0,80	± 1,00	± 0,90	± 1,10	
15	25	± 0,95	± 1,20	± 1,05	± 1,30	± 1,30	± 1,60	
25	50	± 1,30	± 1,60	± 1,40	± 1,75	± 1,50	± 1,90	
50	-	± 1,50	± 1,90	± 1,65	± 2,05	± 1,80	± 2,20	

1) For all materials, except CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R).
 2) For all alloys CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R).



TOLERANCES ON THICKNESS OF COLD-ROLLED PRODUCTS

Nominal Thickness		Thickness tolerances for nominal widths			
Greater than	Up to and including	Up to and including 350	Greater than 350, up to and inc. 700	Greater than 700, up to and inc. 1000	Greater than 1000, up to and inc. 1250
0.1 ^b	0,2	± 0,018	-	-	-
0,2	0,3	± 0,022	± 0,03	± 0,04	-
0,3	0,4	± 0,025	± 0,04	± 0,05	± 0,07
0,4	0,5	± 0,03	± 0,05	± 0,06	± 0,08
0,5	0,8	± 0,04	± 0,06	± 0,07	± 0,09
0,8	1,2	± 0,05	± 0,07	± 0,09	± 0,10
1,2	1,8	± 0,06	± 0,08	± 0,10	± 0,11
1,8	2,5	± 0,07	± 0,09	± 0,11	± 0,13
2,5	3,2	± 0,08	± 0,10	± 0,13	± 0,17
3,2	4,0	± 0,10	± 0,12	± 0,15	± 0,20
4,0	5,0	± 0,12	± 0,14	± 0,17	± 0,23
5,0	6,0	± 0,14	± 0,16	± 0,20	± 0,26
6,0	7,0	± 0,16	± 0,19	± 0,23	± 0,29
7,0	8,0	± 0,18	± 0,22	± 0,26	± 0,32
8,0	9,0	± 0,20	± 0,25	± 0,29	± 0,35
9,0	10,0	± 0,22	± 0,28	± 0,32	± 0,38

^a For all alloys CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R), tolerances on thickness must be multiplied by 1.25 and the result rounded up to 0.01mm

^b includes 0.1.

NOTA - For thicknesses greater than 10mm, tolerances are those indicates in Norm EN 1653.