



BRONMETAL

Bronze Br

Product format:

Sheet

Technical characteristics:

Laminated plates for decorative bronze



TOLERANCES ON THICKNESS OF HOT ROLLED PRODUCTS

Nominal thickness		Tolerances on thickness, for nominal widths of						
Greater than	Up to and including	Up to and inc. 700		Greater than 700 up to and including 1000		Greater than 1000 up to and including 1500		Greater than 1500
		1)	2)	1)	2)	1)	2)	
-	2,5	By agreement		By agreement		By agreement		By agreement
2,5	5,0	± 0,25	± 0,30	± 0,30	± 0,35	± 0,35	± 0,45	
5,0	7,5	± 0,35	± 0,45	± 0,40	± 0,50	± 0,45	± 0,55	
7,5	10	± 0,45	± 0,60	± 0,50	± 0,65	± 0,55	± 0,75	
10	15	± 0,75	± 0,95	± 0,80	± 1,00	± 0,90	± 1,10	
15	25	± 0,95	± 1,20	± 1,05	± 1,30	± 1,30	± 1,60	
25	50	± 1,30	± 1,60	± 1,40	± 1,75	± 1,50	± 1,90	
50	-	± 1,50	± 1,90	± 1,65	± 2,05	± 1,80	± 2,20	
<p>1) For all materials, except CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R)</p> <p>2) For all alloys CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R)</p>								

TOLERANCES ON THICKNESS OF COLD ROLLED PRODUCTS

Nominal thickness		Tolerances on thickness, for nominal widths of			
Greater than	Up to and including	Up to and inc. 350	Greater than 350 up to and including 700	Greater than 700 up to and including 1000	Greater than 1000 up to and including 1250
0.1 ^b	0,2	± 0,018			
0,2	0,3	± 0,022	± 0,03	± 0,04	-
0,3	0,4	± 0,025	± 0,04	± 0,05	± 0,07
0,4	0,5	± 0,03	± 0,05	± 0,06	± 0,08
0,5	0,8	± 0,04	± 0,06	± 0,07	± 0,09
0,8	1,2	± 0,05	± 0,07	± 0,09	± 0,10
1,2	1,8	± 0,06	± 0,08	± 0,10	± 0,11
1,8	2,5	± 0,07	± 0,09	± 0,11	± 0,13
2,5	3,2	± 0,08	± 0,10	± 0,13	± 0,17
3,2	4,0	± 0,10	± 0,12	± 0,15	± 0,20
4,0	5,0	± 0,12	± 0,14	± 0,17	± 0,23
5,0	6,0	± 0,14	± 0,16	± 0,20	± 0,26
6,0	7,0	± 0,16	± 0,19	± 0,23	± 0,29
7,0	8,0	± 0,18	± 0,22	± 0,26	± 0,32
8,0	9,0	± 0,20	± 0,25	± 0,29	± 0,35
9,0	10,0	± 0,22	± 0,28	± 0,32	± 0,38

^a For alloys CuAl8Fe3 (CW303G), CuNi10Fe1Mn (CW352H), CuNi30Mn1Fe (CW354H) y CuZn20Al2As (CW702R), tolerances on thickness must be multiplied by 1.25 and the result rounded up to 0.01mm.

^b Includes 0.1.

NOTE - For thicknesses greater than 10mm, tolerances are those indicated in Norm EN 1653