



**BRONMETAL**

Copper Cu

Product format:

Tape electrical applications

Technical characteristics:

Tape or laminated copper strip for electrical applications



## TOLERANCES

Nominal thickness		Tolerance on nominal thickness to width					
Greater than	Up to and including	from 10 to 200 inclusive		Greater than 200 to 350 inclusive	Greater than 350 to 700 inclusive	Greater than 700 to 1000 inclusive	Greater than 1000 to 1250 inclusive
		normal	Special				
0.05 <sup>a</sup>	0,1	± 10% <sup>b</sup>	-	-	-	-	-
0,1	0,2	± 0,010	± 0,007	± 0,015	-	-	-
0,2	0,3	± 0,015	± 0,010	± 0,020	± 0,03	± 0,04	-
0,3	0,4	± 0,018	± 0,012	± 0,022	± 0,04	± 0,05	± 0,07
0,4	0,5	± 0,020	± 0,015	± 0,025	± 0,05	± 0,06	± 0,08
0,5	0,8	± 0,025	± 0,018	± 0,030	± 0,06	± 0,07	± 0,09
0,8	1,2	± 0,030	± 0,022	± 0,040	± 0,07	± 0,09	± 0,10
1,2	1,8	± 0,035	± 0,028	± 0,06	± 0,08	± 0,10	± 0,11
1,8	2,5	± 0,045	± 0,035	± 0,07	± 0,09	± 0,11	± 0,13
2,5	3,2	± 0,055	± 0,040	± 0,08	± 0,10	± 0,13	± 0,17
3,2	4,0	-	-	± 0,10	± 0,12	± 0,15	± 0,20
4,0	5,0	-	-	± 0,12	± 0,14	± 0,17	± 0,23
5,0	6,0	-	-	± 0,14	± 0,16	± 0,20	± 0,26
6,0	7,0	-	-	± 0,16	± 0,19	± 0,23	± 0,29
7,0	8,0	-	-	± 0,18	± 0,22	± 0,26	± 0,32
8,0	9,0	-	-	± 0,20	± 0,25	± 0,29	± 0,35
9,0	10,0	-	-	± 0,22	± 0,28	± 0,32	± 0,38
10,0	25,0	-	-	± 0,25	± 0,30	± 0,35	± 0,45

<sup>a</sup> Including the value 0.05  
<sup>b</sup> ± 10% of the nominal thickness