



Aluminum Al

Product format:

Laminate

Technical characteristics:

Aluminum sheet and strip rolled

ALUMINIUM ALLOYS SERIES 1000

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-1050A	EN AW-Al 99,5	0,25	0,40	0,05	0,05	0,05	-	-	0,07	0,05	-	-	-	0,03	-	99.50 ^C
EN AW-1060	EN AW-Al 99,6	0,25	0,35	0,05	0,03	0,03	-	-	0,05	0,03	-	0,05	-	0,03	-	99.60 ^C
EN AW-1070A	EN AW-Al 99,7	0,20	0,25	0,03	0,03	0,03	-	-	0,07	0,03	-	-	-	0,03	-	99.70 ^C
EN AW-1080A	EN AW-Al 99,8(A)	0,15	0,15	0,03	0,02	0,02	-	-	0,06	0,02	0,03	-	^E	0,02	-	99.80 ^C
EN AW-1085	EN AW-Al 99,85	0,10	0,12	0,03	0,02	0,02	-	-	0,03	0,02	0,03	0,05	-	0,01	-	99.85 ^C
EN AW-1090	EN AW-Al 99,90	0,07	0,07	0,02	0,01	0,01	-	-	0,03	0,01	0,03	0,05	-	0,01	-	99.90 ^C
EN AW-1098	EN AW-Al 99,98	0,01	0,006	0,003	-	-	-	-	0,015	0,003	-	-	-	0,003	-	99.98 ^D
EN AW-1100	EN AW-Al 99,0Cu	0,95 Si + Fe		0,05-0,20	0,05	-	-	-	0,10	-	-	-	^E	0,05	0,15	99.00 ^C
EN AW-1110	EN AW-Al 99,1	0,30	0,80	0,04	0,01	0,25	0,01	-	-	-	-	-	0,02B;0,03V+Ti	0,03	0,15	99.10 ^C
EN AW-1198	EN AW-Al 99,98(A)	0,01	0,006	0,006	0,006	-	-	-	0,01	0,006	0,006	-	-	0,003	-	99.98 ^D
EN AW-1199	EN AW-Al 99,99	0,006	0,006	0,006	0,002	0,006	-	-	0,006	0,002	0,005	0,005	-	0,002	-	99.99 ^D
EN AW-1200	EN AW-Al 99,0	1,00 Si + Fe		0,05	0,05	-	-	-	0,10	0,05	-	-	^E	0,05	0,15	99.00 ^C
EN AW-1200A	EN AW-Al 99,0(A)	1,00 Si + Fe		0,10	0,30	0,30	0,10	-	0,10	-	-	-	-	0,05	0,15	99.00 ^C
EN AW-1235	EN AW-Al 99,35	0,65 Si + Fe		0,05	0,05	0,05	-	-	0,10	0,06	-	0,05	-	0,03	-	99.35 ^C
EN AW-1350	EN AW-Al 99,5	0,10	0,40	0,05	0,01	-	0,01	-	0,05	-	0,03	-	0,05B;0,02V+Ti	0,03	0,10	99.50 ^C
EN AW-1350A	EN AW-Al 99,5(A)	0,25	0,40	0,02	-	0,05	-	-	0,05	-	-	-	0,03Cr+Mn+Ti+V	0,03	-	99.50 ^C
EN AW-1370	EN AW-Al 99,7	0,10	0,25	0,02	0,01	0,02	0,01	-	0,04	-	0,03	-	0,02B;0,02V+Ti	0,02	0,10	99.70 ^C
EN AW-1450	EN AW-Al 99,5Ti	0,25	0,40	0,05	0,05	0,05	-	-	0,07	0,10-0,20	-	-	^E	0,03	-	99.50 ^C

^A "Others" includes cited elements which have not had a specific limit indicated, as well as non-cited metallic elements. The manufacturer may analyse samples in search of traces of non-specified elements in the records or specifications. However, such analysis is unnecessary and may not cover all elements present in "Others". If analysis by the manufacturer or purchaser establishes that an element of "Others" surpasses the limit of "Each" or that the sum of various elements from "Others" surpasses the limit of "Total", the material must be considered as non-conforming.

^B The sum of "Others" metallic elements whose contents are, in turn, greater or equal to 0.010% expressed to two decimal figures before carrying out the sum.

^C The content of aluminium for the non-alloy which is not obtained from a refining process is equal in the difference between 100.00% and the sum of all the other metallic elements present in similar or greater quantities to 0,0010% each, expressing each adding to two decimal places before the sum.

^D The content of aluminium for the non-alloy which is obtained from a refining process is equal in the difference between 100.00% and the sum of all the other metallic elements present in similar or greater quantities to 0,0010% each, expressing each adding to three decimal places, rounding up the result of the sum to two decimal places before proceeding to the subtraction.

^E 0.0003 max. Be rod electrode and filler wire welding only.

ALEACIONES DE ALUMINIUM SERIE 2000 – AL CU

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-2001	EN AW-Al Cu5,5MgMn	0,20	0,20	5,2-6,0	0,15-0,50	0,20-0,45	0,10	0,05	0,10	0,20	-	-	0.05 Zr ^C	0,05	0,15	Rest
EN AW-2007	EN AW-Al Cu4PbMgMn	0,80	0,80	3,3-4,6	0,50-1,0	0,40-1,8	0,10	0,2	0,80	0,20	-	-	^D	0,10	0,30	Rest
EN AW-2011	EN AW-Al Cu6BiPb	0,40	0,70	5,0-6,0	-	-	-	-	0,30	-	-	-	^E	0,05	0,15	Rest
EN AW-2011A	EN AW-Al Cu6BiPb(A)	0,40	0,50	4,5-6,0	-	-	-	-	0,30	-	-	-	^E	0,05	0,15	Rest
EN AW-2014	EN AW-Al Cu4SiMg	0,5-1,2	0,70	3,9-5,0	0,40-1,2	0,20-0,8	0,10	-	0,25	0,15	-	-	^F	0,05	0,15	Rest
EN AW-2014A	EN AW-Al Cu4SiMg(A)	0,5-0,9	0,50	3,9-5,0	0,40-1,2	0,20-0,8	0,10	0,1	0,25	0,15	-	-	0,20 Zr + Ti	0,05	0,15	Rest
EN AW-2017A	EN AW-Al Cu4MgSi(A)	0,2-0,8	0,70	3,5-4,5	0,40-1,0	0,40-1,0	0,10	-	0,25	-	-	-	0,25 Zr + Ti	0,05	0,15	Rest
EN AW-2024	EN AW-Al Cu4Mg1	0,50	0,50	3,8-4,9	0,30-0,9	1,2-1,8	0,10	-	0,25	0,15	-	-	^F	0,05	0,15	Rest
EN AW-2030	EN AW-Al Cu4PbMg	0,80	0,70	3,3-4,5	0,20-1,0	0,50-1,3	0,10	-	0,50	0,20	-	-	0,20 Bi; 0,8-1,5 Pb	0,10	0,30	Rest
EN AW-2031	EN AW-Al Cu2,5NiMg	0,5-1,3	0,6-1,2	1,8-2,8	0,50	0,6-1,2	-	0,6-1,4	0,20	0,20	-	-	-	0,05	0,15	Rest
EN AW-2091	EN AW-Al Cu2Li2Mg1,5	0,20	0,30	1,8-2,5	0,10	1,1-1,9	0,10	-	0,25	0,10	-	-	0.04-0.16 Zr ^G	0,05	0,15	Rest
EN AW-2117	EN AW-Al Cu2,5Mg	0,80	0,70	2,2-3,0	0,20	0,20-0,50	0,10	-	0,25	-	-	-	-	0,05	0,15	Rest
EN AW-2124	EN AW-Al Cu4Mg1(A)	0,20	0,30	3,8-4,9	0,30-0,9	1,2-1,8	0,10	-	0,25	0,15	-	-	^F	0,05	0,15	Rest
EN AW-2214	EN AW-Al Cu4SiMg(B)	0,5-1,2	0,30	3,9-5,0	0,41-1,2	0,20-0,8	0,10	-	0,25	0,15	-	-	^F	0,05	0,15	Rest
EN AW-2219	EN AW-Al Cu6Mn	0,20	0,30	5,8-6,8	0,20-0,40	0,02	-	-	0,10	0,02-0,10	-	0,05-0,15	0,10-0,25 Zr	0,05	0,15	Rest
EN AW-2319	EN AW-Al Cu6Mn(A)	0,20	0,30	5,8-6,8	0,20-0,40	0,02	-	-	0,10	0,10-0,20	-	0,05-0,15	0.10-0.25 Zr ^H	0,05	0,15	Rest
EN AW-2618A	EN AW-Al Cu2Mg1,5Ni	0,15-0,25	0,9-1,4	1,8-2,7	0,25	1,2-1,8	-	0,8-1,4	0,15	0,20	-	-	0,25 Zr + Ti	0,05	0,15	Rest

^A "Others" includes cited elements which have not had a specific limit indicated, as well as non-cited metallic elements. The manufacturer may analyse samples in search of traces of non-specified elements in the records or specifications. However, such analysis is unnecessary and may not cover all elements present in "Others". If analysis by the manufacturer or purchaser establishes that an element of "Others" surpasses the limit of "Each" or that the sum of varios elements from "Others" surpasses the limit of "Total", the material must be considered as non-conforming.

^B The sum of "Others" metallic elements whose contents are, in turn, greater or equal to 0.010% expressed to two decimal figures before carrying out the sum.

^C 0.003 máx. Pb.

^D 0.20 Bi; 0.8-1.5 Pb; 0.20 Sn.

^E 0.20-0.6 Bi; 0.20-0.6 Pb.

^F A maximum limit of 0.20 for Zr + Ti may be used for extracted and wrought products by agreement between the supplier or the manufacturer and the purchaser.

^G 1.7-2.3 Li.

^H 0.0003 max. Be rod electrode and filler wire welding only

ALEACIONES DE ALUMINIUM SERIE 3000 – AL MN

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-3002	EN AW-Al Mn0,2Mg0,1	0,08	0,1	0,15	0,05-0,25	0,05-0,20	-	-	0,05	0,03	-	0,05	-	0,03	0,10	Rest
EN AW-3003	EN AW-Al Mn1Cu	0,6	0,7	0,05-0,20	1,0-1,5	-	-	-	0,10	-	-	-	-	0,05	0,15	Rest
EN AW-3004	EN AW-Al Mn1Mg1	0,3	0,7	0,25	1,0-1,5	0,8-1,3	-	-	0,25	-	-	-	-	0,05	0,15	Rest
EN AW-3005	EN AW-Al Mn1Mg0,5	0,6	0,7	0,3	1,0-1,5	0,20-0,6	0,10	-	0,25	0,10	-	-	-	0,05	0,15	Rest
EN AW-3005A	EN AW-Al Mn1Mg0,5(A)	0,7	0,8	0,3	1,0-1,5	0,20-0,6	0,10	-	0,40	0,10	-	-	-	0,05	0,15	Rest
EN AW-3017	EN AW-Al Mn1Cu0,3	0,25	0,25-0,45	0,25-0,40	0,8-1,2	0,1	0,15	-	0,10	0,05	-	-	-	0,05	0,15	Rest
EN AW-3102	EN AW-Al Mn0,2	0,4	0,7	0,1	0,05-0,40	-	-	-	0,30	0,10	-	-	-	0,05	0,15	Rest
EN AW-3103	EN AW-Al Mn1	0,5	0,7	0,1	0,9-1,5	0,3	0,10	-	0,20	-	-	-	0,10 Zr + Ti ^C	0,05	0,15	Rest
EN AW-3103A	EN AW-Al Mn1(A)	0,5	0,7	0,1	0,7-1,4	0,3	0,10	-	0,20	0,10	-	-	0,10 Zr + Ti	0,05	0,15	Rest
EN AW-3104	EN AW-Al Mn1Mg1Cu	0,6	0,8	0,05-0,25	0,8-1,4	0,8-1,3	-	-	0,25	0,10	0,05	0,05	-	0,05	0,15	Rest
EN AW-3105	EN AW-Al Mn0,5Mg0,5	0,6	0,7	0,3	0,30-0,8	0,20-0,8	0,20	-	0,40	0,10	-	-	-	0,05	0,15	Rest
EN AW-3105A	EN AW-Al Mn0,5Mg0,5(A)	0,6	0,7	0,3	0,30-0,8	0,20-0,8	0,20	-	0,25	0,10	-	-	-	0,05	0,15	Rest
EN AW-3105B	EN AW-Al Mn0,6Mg0,5	0,7	0,9	0,3	0,30-0,9	0,20-0,8	0,20	-	0,50	0,10	-	-	0,10 Pb	0,05	0,15	Rest
EN AW-3207	EN AW-Al Mn0,6	0,3	0,45	0,1	0,40-0,8	0,1	-	-	0,10	-	-	-	-	0,05	0,15	Rest
EN AW-3207A	EN AW-Al Mn0,6(A)	0,35	0,6	0,25	0,30-0,8	0,4	0,20	-	0,25	-	-	-	-	0,05	0,15	Rest

^A "Others" includes cited elements which have not had a specific limit indicated, as well as non-cited metallic elements. The manufacturer may analyse samples in search of traces of non-specified elements in the records or specifications. However, such analysis is unnecessary and may not cover all elements present in "Others". If analysis by the manufacturer or purchaser establishes that an element of "Others" surpasses the limit of "Each" or that the sum of varios elements from "Others" surpasses the limit of "Total", the material must be considered as non-conforming.

^B The sum of "Others" metallic elements whose contents are, in turn, greater or equal to 0.010% expressed to two decimal figures before carrying out the sum.

^C 0.0003 max. Be rod electrode and filler wire welding only

ALEACIONES DE ALUMINIUM SERIE 4000 – AL SI

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	G a	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-4004	EN AW-Al Si10Mg1,5	9,0-10,5	0,8	0,25	0,1	1,0-2,0	-	-	0,2	-	-	-	-	0,05	0,15	Rest
EN AW-4006	EN AW-Al Si1Fe	0,8-1,2	0,50-0,8	0,1	0,05	0,01	0,2	-	0,05	-	-	-	-	0,05	0,15	Rest
EN AW-4007	EN AW-Al Si1,5Mn	1,0-1,7	0,40-1,0	0,2	0,8-1,5	0,2	0,05-0,25	0,15-0,7	0,1	0,1	-	-	0,05 Co	0,05	0,15	Rest
EN AW-4015	EN AW-Al Si2Mn	1,4-2,2	0,7	0,2	0,6-1,2	0,10-0,50	-	-	0,2	-	-	-	-	0,05	0,15	Rest
EN AW-4016	EN AW-Al Si2MnZn	1,4-2,2	0,7	0,2	0,6-1,2	0,1	-	-	0,50-1,3	-	-	-	-	0,05	0,15	Rest
EN AW-4017	EN AW-Al SiMnMgCu	0,6-1,6	0,7	0,10-0,50	0,6-1,2	0,10-0,50	-	-	0,2	-	-	-	-	0,05	0,15	Rest
EN AW-4018	EN AW-Al Si7Mg	6,5-7,5	0,2	0,05	0,1	0,50-0,8	-	-	0,1	0,2	-	-	^C	0,05	0,15	Rest
EN AW-4032	EN AW-Al Si12,5MgCuNi	11,0-13,5	1,0	0,50-1,3	-	0,8-1,3	0,1	0,50-1,3	0,25	-	-	-	-	0,05	0,15	Rest
EN AW-4043A	EN AW-Al Si5(A)	4,5-6,0	0,6	0,3	0,15	0,2	-	-	0,1	0,15	-	-	^C	0,05	0,15	Rest
EN AW-4045	EN AW-Al Si10	9,0-11,0	0,8	0,3	0,05	0,05	-	-	0,1	0,2	-	-	-	0,05	0,15	Rest
EN AW-4046	EN AW-Al Si10Mg	9,0-11,0	0,5	0,03	0,4	0,20-0,50	-	-	0,1	0,15	-	-	^C	0,05	0,15	Rest
EN AW-4047A	EN AW-Al Si12(A)	11,0-13,0	0,6	0,3	0,15	0,1	-	-	0,2	0,15	-	-	^C	0,05	0,15	Rest
EN AW-4104	EN AW-Al Si10MgBi	9,0-10,5	0,8	0,25	0,1	1,0-2,0	-	-	0,2	-	-	-	0,02-0,20 Bi	0,05	0,15	Rest
EN AW-4343	EN AW-Al Si7,5	6,8-8,2	0,8	0,25	0,1	-	-	-	0,2	-	-	-	-	0,05	0,15	Rest

^A "Others" includes cited elements which have not had a specific limit indicated, as well as non-cited metallic elements. The manufacturer may analyse samples in search of traces of non-specified elements in the records or specifications. However, such analysis is unnecessary and may not cover all elements present in "Others". If analysis by the manufacturer or purchaser establishes that an element of "Others" surpasses the limit of "Each" or that the sum of varios elements from "Others" surpasses the limit of "Total", the material must be considered as non-conforming.

^B The sum of "Others" metallic elements whose contents are, in turn, greater or equal to 0.010% expressed to two decimal figures before carrying out the sum.

^C 0.0003 max. Be rod electrode and filler wire welding only

ALEACIONES DE ALUMINIUM SERIE 5000 – AL MG

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-5005	EN AW-Al Mg1(B)	0,3	0,7	0,2	0,2	0,50-1,1	0,1	-	0,25	-	-	-	-	0,05	0,15	Rest
EN AW-5005A	EN AW-Al Mg1(C)	0,3	0,45	0,05	0,15	0,7-1,1	0,1	-	0,2	-	-	-	-	0,05	0,15	Rest
EN AW-5006	EN AW-Al Mg1Mn0,5	0,4	0,8	0,1	0,40-0,8	0,8-1,3	0,1	-	0,25	0,1	-	-	-	0,05	0,15	Rest
EN AW-5010	EN AW-Al Mg0,5Mn	0,4	0,7	0,25	0,10-0,30	0,20-0,6	0,15	-	0,3	0,1	-	-	-	0,05	0,15	Rest
EN AW-5018	EN AW-Al Mg3Mn0,4	0,25	0,4	0,05	0,20-0,6	2,6-3,6	0,3	-	0,2	0,15	-	-	0.20-0.6 Mn + Cr ^C	0,05	0,15	Rest
EN AW-5019	EN AW-Al Mg5	0,4	0,5	0,1	0,10-0,6	4,5-5,6	0,2	-	0,2	0,2	-	-	0.10-0.6 Mn + Cr	0,05	0,15	Rest
EN AW-5026	EN AW-Al Mg4,5MnSiFe	0,55-1,4	0,20-1,0	0,10-0,8	0,6-1,8	3,9-4,9	0,3	-	1,0	0,2	-	-	0,30 Zr	0,05	0,15	Rest
EN AW-5040	EN AW-Al Mg1,5Mn	0,3	0,7	0,25	0,9-1,4	1,0-1,5	0,10-0,30	-	0,25	-	-	-	-	0,05	0,15	Rest
EN AW-5042	EN AW-Al Mg3,5Mn	0,2	0,35	0,15	0,20-0,50	3,0-4,0	0,1	-	0,25	0,1	-	-	-	0,05	0,15	Rest
EN AW-5049	EN AW-Al Mg2Mn0,8	0,4	0,5	0,1	0,50-1,1	1,6-2,5	0,3	-	0,2	0,1	-	-	-	0,05	0,15	Rest
EN AW-5050	EN AW-Al Mg1,5 (C)	0,4	0,7	0,2	0,1	1,1-1,8	0,1	-	0,25	-	-	-	-	0,05	0,15	Rest
EN AW-5050A	EN AW-Al Mg1,5(D)	0,4	0,7	0,2	0,3	1,1-1,8	0,1	-	0,25	-	-	-	-	0,05	0,15	Rest
EN AW-5051A	EN AW-Al Mg2(B)	0,3	0,45	0,05	0,25	1,4-2,1	0,3	-	0,2	0,1	-	-	-	0,05	0,15	Rest
EN AW-5052	EN AW-Al Mg2,5	0,25	0,4	0,1	0,1	2,2-2,8	0,15-0,35	-	0,1	-	-	-	-	0,05	0,15	Rest
EN AW-5058	EN AW-Al Mg5Pb1,5	0,4	0,5	0,1	0,2	4,5-5,6	0,1	-	0,2	0,2	-	-	1,2-1,8 Pb	0,05	0,15	Rest
EN AW-5059	EN AW-Al Mg5,5MnZnZr	0,45	0,5	0,25	0,6-1,2	5,0-6,0	0,25	-	0,40-0,9	0,2	-	-	0,05-0,25 Zr	0,05	0,15	Rest
EN AW-5070	EN AW-Al Mg4MnZn	0,25	0,4	0,25	0,40-0,8	3,5-4,5	0,3	-	0,40-0,8	0,15	-	-	-	0,05	0,15	Rest
EN AW-5082	EN AW-Al Mg4,5	0,2	0,35	0,15	0,15	4,0-5,0	0,15	-	0,25	0,1	-	-	-	0,05	0,15	Rest
EN AW-5083	EN AW-Al Mg4,5Mn0,7	0,4	0,4	0,1	0,40-1,0	4,0-4,9	0,05-0,25	-	0,25	0,15	-	-	-	0,05	0,15	Rest
EN AW-5086	EN AW-Al Mg4	0,4	0,5	0,1	0,20-0,7	3,5-4,5	0,05-0,25	-	0,25	0,15	-	-	-	0,05	0,15	Rest
EN AW-5087	EN AW-Al Mg4,5MnZr	0,25	0,4	0,05	0,7-1,1	4,5-5,2	0,05-0,25	-	0,25	0,15	-	-	0.10-0.20 Zr ^C	0,05	0,15	Rest
EN AW-5088	EN AW-Al Mg5Mn0,4	0,2	0,10-0,35	0,25	0,20-0,50	4,7-5,5	0,15	-	0,20-0,40	-	-	-	0,15 Zr	0,05	0,15	Rest
EN AW-5110	EN AW-Al 99,85Mg0,5	0,08	0,08	-	0,03	0,30-0,6	-	-	0,05	0,02	-	-	-	0,02	-	Rest

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-5119	EN AW-Al Mg5(A)	0,25	0,4	0,05	0,20-0,6	4,5-5,6	0,3	-	0,2	0,15	-	-	0.20-0.6 Mn + Cr ^C	0,05	0,15	Rest
EN AW-5119A	EN AW-Al Mg5(B)	0,25	0,4	0,05	0,20-0,6	4,5-5,6	0,3	-	0,2	0,15			0.20-0.6 Mn + Cr ^E	0,05	0,15	Rest
EN AW-5149	EN AW-Al Mg2Mn0,8(A)	0,25	0,4	0,05	0,50-1,1	1,6-2,5	0,3	-	0,2	0,15	-	-	-	0,05	0,15	Rest
EN AW-5154A	EN AW-Al Mg3,5(A)	0,5	0,5	0,1	0,5	3,1-3,9	0,25	-	0,2	0,2	-	-	0.10-0,5 Mn + Cr ^C	0,05	0,15	Rest
EN AW-5154B	EN AW-Al Mg3,5Mn0,3	0,35	0,45	0,05	0,15-0,45	3,2-3,8	0,1	0,01	0,15	0,15	-	-	-	0,05	0,15	Rest
EN AW-5182	EN AW-Al Mg4,5Mn0,4	0,2	0,35	0,15	0,20-0,50	4,0-5,0	0,1	-	0,25	0,1	-	-	-	0,05	0,15	Rest
EN AW-5183	EN AW-Al Mg4,5Mn0,7(A)	0,4	0,4	0,1	0,50-1	4,3-5,2	0,05-0,25	-	0,25	0,15	-	-	^C	0,05	0,15	Rest
EN AW-5183A	EN AW-Al Mg4,5Mn0,7(C)	0,4	0,4	0,1	0,50-1	4,3-5,2	0,05-0,25	-	0,25	0,15	-	-	^E	0,05	0,15	Rest
EN AW-5186	EN AW-Al Mg4Mn0,4	0,4	0,45	0,25	0,20-0,50	3,8-4,8	0,15	-	0,4	0,15	-	-	0,05 Zr	0,05	0,15	Rest
EN AW-5187	EN AW-Al Mg4,5MnZr	0,25	0,4	0,05	0,7-1,1	4,5-5,2	0,05-0,25	-	0,25	0,15	-	-	0.10-0.20 Zr ^E	0,05	0,15	Rest
EN AW-5210	EN AW-Al 99,9Mg0,5	0,06	0,04	-	0,03	0,35-0,6	-	-	0,04	0,01	-	-	-	0,01	-	Rest
EN AW-5249	EN AW-Al Mg2Mn0,8Zr	0,25	0,4	0,05	0,50-1,1	1,6-2,5	0,3	-	0,2	0,15	-	-	0.10-0.20 Zr ^C	0,05	0,15	Rest
EN AW-5251	EN AW-Al Mg2Mn0,3	0,4	0,5	0,15	0,10-0,50	1,7-2,4	0,15	-	0,15	0,15	-	-	-	0,05	0,15	Rest
EN AW-5252	EN AW-Al Mg2,5(B)	0,08	0,1	0,1	0,1	2,2-2,8	-	-	0,05	-	-	0,05	-	0,03	0,10	Rest
EN AW-5283A	EN AW-Al Mg4,5Mn0,7(B)	0,3	0,3	0,03	0,50-1	4,5-5,1	0,05	0,03	0,1	0,03	-	-	0.05 Zr ^D	0,05	0,15	Rest
EN AW-5305	EN AW-Al 99,85Mg1	0,08	0,08	-	0,03	0,7-1,1		-	0,05	0,02	-	-	-	0,02	-	Rest
EN AW-5310	EN AW-Al 99,98Mg0,5	0,01	0,008	-	-	0,35-0,6	-	-	0,01	0,008	-	-	0,008 Fe + Ti	0,003	-	Rest
EN AW-5352	EN AW-Al Mg2,5(A)	0,45 Si + Fe		0,1	0,1	2,2-2,8	0,1	-	0,1	0,1	-	-	-	0,05	0,15	Rest
EN AW-5354	EN AW-Al Mg2,5MnZr	0,25	0,4	0,05	0,50-1	2,4-3,0	0,05-0,20	-	0,25	0,15	-	-	0,10-0,20 Zr	0,05	0,15	Rest
EN AW-5356	EN AW-Al Mg5Cr(A)	0,25	0,4	0,1	0,05-0,2	4,5-5,5	0,05-0,20	-	0,1	0,06-0,20	-	-	^C	0,05	0,15	Rest
EN AW-5356A	EN AW-Al Mg5Cr(B)	0,25	0,4	0,1	0,05-0,2	4,5-5,5	0,05-0,20	-	0,1	0,06-0,20	-	-	^E	0,05	0,15	Rest
EN AW-5383	EN AW-Al Mg4,5Mn0,9	0,25	0,25	0,2	0,7-1	4,0-5,2	0,25	-	0,4	0,15	-	-	0,20 Zr	0,05	0,15	Rest
EN AW-5449	EN AW-Al Mg2Mn0,8(B)	0,4	0,7	0,3	0,6-1,1	1,6-2,6	0,3	-	0,3	0,1	-	-	-	0,05	0,15	Rest
EN AW-5454	EN AW-Al Mg3Mn	0,25	0,4	0,1	0,50-1	2,4-3,0	0,05-0,20	-	0,25	0,2	-	-	-	0,05	0,15	Rest
EN AW-5456	EN AW-Al Mg5Mn1	0,25	0,4	0,1	0,50-1	4,7-5,5	0,05-0,20	-	0,25	0,2	-	-	-	0,05	0,15	Rest

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-5456A	EN AW-Al Mg5Mn1(A)	0,25	0,4	0,05	0,7-1,1	4,5-5,2	0,05-0,25	-	0,25	0,15	-	-	^C	0,05	0,15	Rest
EN AW-5456B	EN AW-Al Mg5Mn1(B)	0,25	0,4	0,05	0,7-1,1	4,5-5,2	0,05-0,25	-	0,25	0,15	-	-	^E	0,05	0,15	Rest
EN AW-5505	EN AW-Al 99,9Mg1	0,06	0,4	-	0,03	0,8-1,1		-	0,04	0,01	-	-	-	0,01	-	Rest
EN AW-5554	EN AW-Al Mg3Mn(A)	0,25	0,4	0,1	0,50-1,0	2,4-3,0	0,05-0,20	-	0,25	0,05-0,20	-	-	^C	0,05	0,15	Rest
EN AW-5556A	EN AW-Al Mg5Mn	0,25	0,4	0,1	0,6-1,0	5,0-5,5	0,05-0,20	-	0,2	0,05-0,20	-	-	^C	0,05	0,15	Rest
EN AW-5556B	EN AW-Al Mg5Mn(A)	0,25	0,4	0,1	0,6-1,0	5,0-5,5	0,05-0,20	-	0,2	0,05-0,20	-	-	^E	0,05	0,15	Rest
EN AW-5605	EN AW-Al 99,98Mg1	0,01	0,008	-	-	0,8-1,1		-	0,01	0,008	-	-	0,008 Fe + Ti	0,003	-	Rest
EN AW-5654	EN AW-Al Mg3,5Cr	0,45 Si + Fe		0,05	0,01	3,1-3,9	0,15-0,35	-	0,2	0,05-0,15	-	-	^C	0,05	0,15	Rest
EN AW-5654A	EN AW-Al Mg3,5Cr(A)	0,45 Si + Fe		0,05	0,01	3,1-3,9	0,15-0,35	-	0,2	0,05-0,15	-	-	^E	0,05	0,15	Rest
EN AW-5657	EN AW-Al 99,85Mg1(A)	0,08	0,1	0,1	0,03	0,6-1,0	-	-	0,05	-	0,03	0,05	-	0,02	0,05	Rest
EN AW-5754	EN AW-Al Mg3	0,4	0,4	0,1	0,5	2,6-3,6	0,3	-	0,2	0,15	-	-	0.10-0.6 Mn + Cr ^C	0,05	0,15	Rest

^A "Others" includes cited elements which have not had a specific limit indicated, as well as non-cited metallic elements. The manufacturer may analyse samples in search of traces of non-specified elements in the records or specifications. However, such analysis is unnecessary and may not cover all elements present in "Others". If analysis by the manufacturer or purchaser establishes that an element of "Others" surpasses the limit of "Each" or that the sum of varios elements from "Others" surpasses the limit of "Total", the material must be considered as non-conforming.

^B The sum of "Others" metallic elements whose contents are, in turn, greater or equal to 0.010% expressed to two decimal figures before carrying out the sum.

^C 0.0003 max. Be rod electrode and filler wire welding only

^D 0.003 máx. Pb.

^E 0.0005 max. Be rod electrode and filler wire welding only

ALEACIONES DE ALUMINIUM SERIE 6000 – AL MG SI

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-6003	EN AW-Al Mg1Si0,8	0,35-1,0	0,6	0,1	0,8	0,8-1,5	0,35	-	0,20	0,10	-	-	-	0,05	0,15	Rest
EN AW-6005	EN AW-Al SiMg	0,6-0,9	0,35	0,1	0,1	0,40-0,6	0,1	-	0,10	0,10	-	-	-	0,05	0,15	Rest
EN AW-6005A	EN AW-Al SiMg(A)	0,50-0,9	0,35	0,3	0,5	0,40-0,7	0,3	-	0,20	0,10	-	-	0,12-0,50 Mn + Cr	0,05	0,15	Rest
EN AW-6005B	EN AW-Al SiMg(B)	0,45-0,8	0,3	0,1	0,1	0,40-0,8	0,1	-	0,10	0,10	-	-	-	0,05	0,15	Rest
EN AW-6008	EN AW-Al SiMgV	0,50-0,9	0,35	0,3	0,3	0,40-0,7	0,3	-	0,20	0,10	-	0,05-0,20	-	0,05	0,15	Rest
EN AW-6011	EN AW-Al Mg0,9Si0,9Cu	0,6-1,2	1	0,40-0,9	0,8	0,6-1,2	0,3	0,20	1,50	0,20	-	-	-	0,05	0,15	Rest
EN AW-6012	EN AW-Al MgSiPb	0,6-1,4	0,5	0,1	0,40-1,0	0,6-1,2	0,3	-	0,30	0,20	-	-	0,7 Bi; 0,40-2,0 Pb	0,05	0,15	Rest
EN AW-6012A	EN AW-Al MgSiSn	0,6-1,4	0,5	0,4	0,20-1,0	0,6-1,2	0,3	-	0,30	0,20	-	-	0,7 Bi; 0,40-2,0 Sn	0,05	0,15	Rest
EN AW-6013	EN AW-Al Mg1Si0,8CuMn	0,6-1,0	0,5	0,6-1,1	0,20-0,8	0,8-1,2	0,1	-	0,25	0,10	-	-	-	0,05	0,15	Rest
EN AW-6014	EN AW-Al Mg0,6Si0,6V	0,30-0,6	0,35	0,25	0,05-0,20	0,40-0,8	0,2	-	0,10	0,10	-	0,05-0,20	-	0,05	0,15	Rest
EN AW-6015	EN AW-Al Mg1Si0,3Cu	0,20-0,40	0,10-0,30	0,10-0,25	0,1	0,8-1,1	0,1	-	0,10	0,10	-	-	-	0,05	0,15	Rest
EN AW-6016	EN AW-Al Si1,2Mg0,4	1,0-1,5	0,5	0,2	0,2	0,25-0,6	0,1	-	0,20	0,15	-	-	-	0,05	0,15	Rest
EN AW-6018	EN AW-Al Mg1SiPbMn	0,50-1,2	0,7	0,15-0,40	0,30-0,8	0,6-1,2	0,1	-	0,30	0,20	-	-	^C	0,05	0,15	Rest
EN AW-6023	EN AW-Al Si1Sn1MgBi	0,6-1,4	0,5	0,20-0,50	0,20-0,6	0,40-0,9	-	-	-	-	-	-	0,30-0,8 Bi; 0,6-1,2 Sn	0,05	0,15	Rest
EN AW-6025	EN AW-Al Mg2,5SiMnCu	0,8-1,5	0,7	0,20-0,7	0,6-1,4	2,1-3,0	0,2	-	0,50	0,2	-	-	-	0,05	0,15	Rest
EN AW-6056	EN AW-Al Si1MgCuMn	0,7-1,3	0,5	0,50-1,1	0,40-1,0	0,6-1,2	0,25	-	0,10-0,7	d	-	-	^D	0,05	0,15	Rest
EN AW-6060	EN AW-Al MgSi	0,30-0,6	0,10-0,30	0,1	0,1	0,35-0,6	0,05	-	0,15	0,10	-	-	-	0,05	0,15	Rest
EN AW-6061	EN AW-Al Mg1SiCu	0,40-0,8	0,7	0,15-0,40	0,15	0,8-1,2	0,04-0,35	-	0,25	0,15	-	-	-	0,05	0,15	Rest
EN AW-6061A	EN AW-Al Mg1SiCu(A)	0,40-0,8	0,7	0,15-0,40	0,15	0,8-1,2	0,04-0,35	-	0,25	0,15	-	-	^E	0,05	0,15	Rest
EN AW-6063	EN AW-Al Mg0,7Si	0,20-0,6	0,35	0,1	0,1	0,45-0,9	0,1	-	0,10	0,10	-	-	-	0,05	0,15	Rest
EN AW-6063A	EN AW-Al Mg0,7Si(A)	0,30-0,6	0,15-0,35	0,1	0,15	0,6-0,9	0,05	-	0,15	0,10	-	-	-	0,05	0,15	Rest
EN AW-6065	EN AW-Al Mg1Bi1Si	0,40-0,8	0,7	0,15-0,40	0,15	0,8-1,2	0,15	-	0,25	0,10	-	-	0,50-1,5 Bi; 0,05 Pb; 0,15 Zr	0,05	0,15	Rest

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-6081	EN AW-Al Si0,9MgMn	0,7-1,1	0,5	0,1	0,10-0,45	0,6-1,0	0,1	-	0,2	0,15	-	-	-	0,05	0,15	Rest
EN AW-6082	EN AW-Al Si1MgMn	0,7-1,3	0,5	0,1	0,40-1,0	0,6-1,2	0,25	-	0,2	0,1	-	-	-	0,05	0,15	Rest
EN AW-6082A	EN AW-Al Si1MgMn(A)	0,7-1,3	0,5	0,1	0,40-1,0	0,6-1,2	0,25	-	0,2	0,1	-	-	^E	0,05	0,15	Rest
EN AW-6101	EN AW-Al MgSi	0,30-0,7	0,5	0,1	0,03	0,35-0,8	0,03	-	0,1	-	-	-	0,06 B	0,03	0,10	Rest
EN AW-6101A	EN AW-Al MgSi(A)	0,30-0,7	0,4	0,05	-	0,40-0,9	-	-	-	-	-	-	-	0,03	0,10	Rest
EN AW-6101B	EN AW-Al MgSi(B)	0,30-0,6	0,10-0,30	0,05	0,05	0,35-0,6	-	-	0,1	-	-	-	-	0,03	0,10	Rest
EN AW-6106	EN AW-Al MgSiMn	0,30-0,6	0,35	0,25	0,05-0,20	0,40-0,8	0,2	-	0,1	-	-	-	-	0,05	0,10	Rest
EN AW-6110A	EN AW-Al Mg0,9MnCu	0,7-1,1	0,5	0,30-0,8	0,30-0,9	0,7-1,1	0,05-0,25	-	0,2	-	-	-	0,20 Ti + Zr	0,05	0,15	Rest
EN AW-6181	EN AW-Al SiMg0,8	0,8-1,2	0,45	0,1	0,15	0,6-1,0	0,1	-	0,2	0,1	-	-	-	0,05	0,15	Rest
EN AW-6182	EN AW-Al Si1MgZr	0,9-1,3	0,5	0,1	0,50-1,0	0,7-1,2	0,25	-	0,2	0,1	-	-	0,05-0,20 Zr	0,05	0,15	Rest
EN AW-6201	EN AW-Al Mg0,7Si	0,50-0,9	0,5	0,1	0,03	0,6-0,9	0,03	-	0,1	-	-	-	0,06 B	0,03	0,10	Rest
EN AW-6261	EN AW-Al Mg1SiCuMn	0,40-0,7	0,4	0,15-0,40	0,20-0,35	0,7-1,0	0,1	-	0,2	0,1	-	-	-	0,05	0,15	Rest
EN AW-6262	EN AW-Al Mg1SiPb	0,40-0,8	0,7	0,15-0,40	0,15	0,8-1,2	0,04-0,14	-	0,25	0,15	-	-	^F	0,05	0,15	Rest
EN AW-6262A	EN AW-Al Mg1SiSn	0,40-0,8	0,7	0,15-0,40	0,15	0,8-1,2	0,04-0,14	-	0,25	0,1	-	-	0,40-0,9Bi; 0,40-1,0 Sn	0,05	0,15	Rest
EN AW-6351	EN AW-Al SiMg0,5Mn	0,7-1,3	0,5	0,1	0,40-0,8	0,40-0,8	-	-	0,2	0,2	-	-	-	0,05	0,15	Rest
EN AW-6351A	EN AW-Al SiMg0,5Mn(A)	0,7-1,3	0,5	0,1	0,40-0,8	0,40-0,8	-	-	0,2	0,2	-	-	^E	0,05	0,15	Rest
EN AW-6360	EN AW-Al SiMgMn	0,35-0,8	0,10-0,30	0,15	0,02-0,15	0,25-0,45	0,05	-	0,1	0,1	-	-	-	0,05	0,15	Rest
EN AW-6401	EN AW-Al 99,9MgSi	0,35-0,7	0,04	0,05-0,20	0,03	0,35-0,7	-	-	0,04	0,01	-	-	-	0,01	-	Rest
EN AW-6463	EN AW-Al Mg0,7Si(B)	0,20-0,6	0,15	0,2	0,05	0,45-0,9	-	-	0,05	-	-	-	-	0,05	0,15	Rest
EN AW-6951	EN AW-Al MgSi0,3Cu	0,20-0,50	0,8	0,15-0,40	0,1	0,40-0,8	-	-	0,2	-	-	-	-	0,05	0,15	Rest

^A "Others" includes cited elements which have not had a specific limit indicated, as well as non-cited metallic elements. The manufacturer may analyse samples in search of traces of non-specified elements in the records or specifications. However, such analysis is unnecessary and may not cover all elements present in "Others". If analysis by the manufacturer or purchaser establishes that an element of "Others" surpasses the limit of "Each" or that the sum of varios elements from "Others" surpasses the limit of "Total", the material must be considered as non-conforming.

^B The sum of "Others" metallic elements whose contents are, in turn, greater or equal to 0.010% expressed to two decimal figures before carrying out the sum.

^C 0.40-0. Bi; 0.40-1.2 Pb.

^D 0.20 máx. Zr + Ti.

^E 0.003 máx. Pb.

^F 0.40-0.7 Bi; 0.40-0.7 Pb.

ALEACIONES DE ALUMINIUM SERIE 7000 – AL ZN

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-7003	EN AW-Al Zn6 Mg0,8Zr	0,3	0,35	0,2	0,3	0,5-1,0	0,2	-	5,0-6,5	0,2	-	-	0,05-0,25 Zr	0,05	0,15	Rest
EN AW-7005	EN AW-Al Zn4,5Mg1,5Mn	0,35	0,4	0,1	0,20-0,7	1,0-1,8	0,06-0,20	-	4,0-5,0	0,01-0,06	-	-	0,08-0,20 Zr	0,05	0,15	Rest
EN AW-7009	EN AW-Al Zn5,5MgCuAg	0,2	0,2	0,6-1,3	0,1	2,1-2,9	0,10-0,25	-	5,5-6,5	0,2	-	-	^C	0,05	0,15	Rest
EN AW-7010	EN AW-Al Zn6MgCu	0,12	0,15	1,5-2,0	0,1	2,1-2,6	0,05	0,05	5,7-6,7	0,06	-	-	0,10-0,16 Zr	0,05	0,15	Rest
EN AW-7012	EN AW-Al Zn6Mg2Cu	0,15	0,25	0,8-1,2	0,08-0,15	1,8-2,2	0,04	-	5,8-6,5	0,02-0,08	-	-	0,10-0,18 Zr	0,05	0,15	Rest
EN AW-7015	EN AW-Al Zn5Mg1,5CuZr	0,2	0,3	0,06-0,15	0,1	1,3-2,1	0,15	-	4,6-5,2	0,1	-	-	0,10-0,20 Zr	0,05	0,15	Rest
EN AW-7016	EN AW-Al Zn4,5Mg1Cu	0,1	0,12	0,45-1,0	0,03	0,8-1,4	-	-	4,0-5,0	0,03	-	0,05	-	0,03	0,10	Rest
EN AW-7019	EN AW-Al Zn4Mg2	0,35	0,45	0,2	0,15-0,5	1,5-2,5	0,2	0,1	3,5-4,5	0,15	-	-	0,10-0,25 Zr	0,05	0,15	Rest
EN AW-7020	EN AW-Al Zn4,5Mg1	0,35	0,4	0,2	0,05-0,5	1,0-1,4	0,10-0,35	-	4,0-5,0	-	-	-	^D	0,05	0,15	Rest
EN AW-7021	EN AW-Al Zn5,5Mg1,5	0,25	0,4	0,25	0,1	1,2-1,8	0,05	-	5,0-6,0	0,1	-	-	0,08-0,18 Zr	0,05	0,15	Rest
EN AW-7022	EN AW-Al Zn5Mg3Cu	0,5	0,5	0,50-1,0	0,10-0,40	2,6-3,7	0,10-0,30	-	4,3-5,2	-	-	-	0,20 Ti + Zr	0,05	0,15	Rest
EN AW-7026	EN AW-Al Zn5Mg1,5Cu	0,08	0,12	0,6-0,9	0,05-0,20	1,5-1,9	-	-	4,6-5,2	0,05	-	-	0,09-0,14 Zr	0,03	0,10	Rest
EN AW-7029	EN AW-Al Zn4,5Mg1,5Cu	0,1	0,12	0,50-0,9	0,03	1,3-2,0	-	-	4,2-5,2	0,05	-	0,05	-	0,03	0,10	Rest
EN AW-7030	EN AW-Al Zn5,5Mg1Cu	0,2	0,3	0,20-0,40	0,05	1,0-1,5	0,04	-	4,8-5,9	0,03	0,03	-	0,03 Zr	0,05	0,15	Rest
EN AW-7039	EN AW-Al Zn4Mg3	0,3	0,4	0,1	0,10-0,40	2,3-3,3	0,15-0,25	-	3,4-4,5	0,1	-	-	-	0,05	0,15	Rest
EN AW-7049A	EN AW-Al Zn8MgCu	0,4	0,5	1,2-1,9	0,5	2,1-3,1	0,05-0,25	-	7,2-8,4	-	-	-	0,25 Zr + Ti	0,05	0,15	Rest
EN AW-7050	EN AW-Al Zn6CuMgZr	0,12	0,15	2,0-2,6	0,1	1,9-2,6	0,04	-	5,7-6,7	0,06	-	-	0,08-0,15 Zr	0,05	0,15	Rest
EN AW-7060	EN AW-Al Zn7CuMg	0,15	0,2	1,8-2,6	0,2	1,3-2,1	0,15-0,25	-	6,1-7,5	0,05	-	-	0,05 Zr ^E	0,05	0,15	Rest
EN AW-7072	EN AW-Al Zn1	0,7 Si + Fe		0,1	0,1	0,1	-	-	0,8-1,3	-	-	-	-	0,05	0,15	Rest
EN AW-7075	EN AW-Al Zn5,5MgCu	0,4	0,5	1,2-2,0	0,3	2,1-2,9	0,18-0,28	-	5,1-6,1	0,2	-	-	^F	0,05	0,15	Rest
EN AW-7108	EN AW-Al Zn5Mg1Zr	0,1	0,1	0,05	0,05	0,7-1,4	-	-	4,5-5,5	0,05	-	-	0,12-0,25 Zr	0,05	0,15	Rest
EN AW-7108A	EN AW-Al Zn5Mg1Zr	0,2	0,3	0,05	0,05	0,7-1,5	0,04	-	4,8-5,8	0,03	0,03	-	0,15-0,25 Zr	0,05	0,15	Rest
EN AW-7116	EN AW-Al Zn4,5Mg1Cu0,8	0,15	0,3	0,50-1,1	0,05	0,8-1,4	-	-	4,2-5,2	0,05	0,03	0,05	-	0,05	0,15	Rest
EN AW-7129	EN AW-Al Zn4,5Mg1,5Cu(A)	0,15	0,3	0,5-0,9	0,1	1,3-2,0	0,1	-	4,2-5,2	0,05	0,03	0,05	-	0,05	0,15	Rest
EN AW-7149	EN AW-Al Zn8MgCu(A)	0,15	0,2	1,2-1,9	0,2	2,0-2,9	0,10-0,22	-	7,2-8,2	0,1	-	-	-	0,05	0,15	Rest
EN AW-7150	EN AW-Al Zn6CuMgZr(A)	0,12	0,15	1,9-2,5	0,1	2,0-2,7	0,04	-	5,9-6,9	0,06	-	-	0,08-0,15 Zr	0,05	0,15	Rest

Designation of the alloy		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Notes	Others ^A		Aluminium
Numerical	Symbolic													Each	Total ^B	mín.
EN AW-7175	EN AW-Al Zn5,5MgCu(B)	0,15	0,2	1,2-2,0	0,1	2,1-2,9	0,18-0,28	-	5,1-6,1	0,1	-	-	-	0,05	0,15	
EN AW-7178	EN AW-Al Zn7MgCu	0,4	0,5	1,6-2,4	0,3	2,4-3,1	0,18-0,28	-	6,3-7,3	0,2	-	-	-	0,05	0,15	
EN AW-7475	EN AW-Al Zn5,5MgCu(A)	0,1	0,12	1,2-1,9	0,06	1,9-2,6	0,18-0,25	-	5,2-6,2	0,06	-	-	-	0,05	0,15	

^A "Others" includes cited elements which have not had a specific limit indicated, as well as non-cited metallic elements. The manufacturer may analyse samples in search of traces of non-specified elements in the records or specifications. However, such analysis is unnecessary and may not cover all elements present in "Others". If analysis by the manufacturer or purchaser establishes that an element of "Others" surpasses the limit of "Each" or that the sum of varios elements from "Others" surpasses the limit of "Total", the material must be considered as non-conforming.

^B The sum of "Others" metallic elements whose contents are, in turn, greater or equal to 0.010% expressed to two decimal figures before carrying out the sum.

^C 0.25-0.40 Ag.

^D 0.08-0.20Zr; 0.08-0.25 Zr + Ti.

^E 0.003 máx. Pb.

^F A maximum limit of 0.25 para Zr + Ti para los productos extruidos y forjados previo acuerdo entre el suministrador o fabricante y el comprador.