



BRONMETAL

Aluminium Al

Product format:

Extruded

Technical characteristics :

Flats, rods, tubes and extruded aluminium profiles



EQUIVALENCES 1050 PURE ALUMINIUM (99,5%)

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------|---------|----------|--------|----------------|--------|-------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AI-99,5 | L-3051 | Al-99,5 | Al-99,5 | | A5 | 1B | 9001/2 | 17010 |
| | Puraltok 99,5 | 3,0255 | 1S | | | Durcilium T | | 4007 |
| | | WG-1S | | | | Hiduminium | | A1 |
| | | 1150/55 | | | | Impalco 0,5 | | Aluran 99,5 |

EQUIVALENCES 1200 PURE ALUMINIUM (99 %)

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|-------------|---------|--------|----------|--------|----------------|--------|-----------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AI 99,0 | L-3001 | Al 99,0 | 2S | 1100 | A-4 | 1C | 3567 | 4010 |
| | Puraltok 99 | 3,0205 | | | | 2S | 1100 | 5090 |
| | | WG-2S | | | | Birmetal 2 | 9001/1 | 17005 |
| | | 90 | | | | Hiduminium-1C | | 1008 |
| | | 1010 | | | | | | NA-2S |
| | | 1191 | | | | | | 2584 |
| | | | | | | | | A0 |
| | | | | | | | | Aluran 99 |

EQUIVALENCES 2007 ALUMINIUM-COPPER

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | |
|--|--------------|--------|--------------|
| SPAIN | GERMANY | FRANCE | SUIZA |
| L-3121 | DIN 1725 | A U4Pb | Al-CuMgPb |
| Cobreltok 07 | DIN 1746 | | Al-CuMgCd |
| | DIN 1747 | | Decotal 200 |
| | Tordal 1970 | | Aludur D 505 |
| | Spanal 320 | | MFK |
| | Aludur 570 A | | |
| | Automat | | |

EQUIVALENCES 2011 ALUMINIUM-COPPER

| COMMERCIAL EQUIVALENT | | | | | | |
|-----------------------|----------|------------|-------------|-------------|------------|----------------|
| SPAIN | CANADA | E.E.U.U. | FRANCE | SUIZA | ITALY | UNITED KINGDOM |
| L-3192 | CB 60 | 2011 | A-U5PbBi | Decotal 500 | Recidal 11 | 28 S |
| 28-S | CSA HA,5 | ASTM B 211 | Fortal 2011 | | | |
| | 28 S | QQ-R-225/3 | | | | |
| | | QQ-R-365 | | | | |
| | | WW-P-471 | | | | |
| | | Ty III | | | | |
| | | QQ-R-566 | | | | |

EQUIVALENCES 2030 ALUMINIUM-COPPER

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | |
|--|--------------|----------------|--------------|
| SPAIN | GERMANY | FRANCE | SUIZA |
| L-3121 | Al CuMgPb | A U4Pb | Al-CuMgPb |
| | 3,1645 | NF A 57.350 | Al-CuMgCd |
| | DIN 1725 | Fortal D | Decotal 200 |
| | DIN 1746 | Fortal 2030 | Aludur D 505 |
| | DIN 1747 | Carbium al Pbl | MFK |
| | Tordal 1970 | Duralumin DE | |
| | Spanal 320 | | |
| | Aludur 570 A | | |
| | Automat | | |

EQUIVALENCES2014 ALUMINIUM-COPPER

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|-------------|--------|-------------------|----------------|----------------|--------|-------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlCu4SiMg | L-313 | 17/14 | CS41M | ASTM B209/210/211 | AU4SG | 2014A-3L62 | 14 S | 17105 |
| | Alucor 66 | 17/16 | CS41N | ASTM B221/241/247 | Duralumin RS | GB 26S | FD 14 | PA33 |
| | Earlumin 44 S | AK3-AK34 | 26 S | MILL-A-22771 | Carbium dur | AWCO 305 | AV 14 | 4338 |
| | B56S | 2140 | 24430 | QQ-A-200/2 | Durcilium fort | Birmetal-478 | SD 14 | Avional 660 |
| | Cobrealtok 14 | 1826/27 | CG42 | QQ-A-225/4 | | BA 305 | 9002/3 | Aludur 570 |
| | | Avional 662 | | QQ-A-250/4 | | Durcilium K | | 26S |
| | | | | | | Hiduminium 66 | | Alradur SI |
| | | | | | | | | 6305 |
| | | | | | | | | 2595 |

EQUIVALENCES 2017 A ALUMINIUM-COPPER

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------------|--------|------------|---------------|----------------|-------------|-------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlCu4Mg1Si | Alucor 101 | Aludur 570 | CM 41A | CM 41A | Duralumin | Durcilium 11 | AV 22 | Avional 100 |
| | Earlumin 40G | Avional 100 | 17S | ASTM B211 | Rivadural 440 | Hiduminium 01 | Avional 22 | Avional 102 |
| | 17S | AK1-AK13 | | ASTM B316 | Carbium | Bimetal 477 | Chitonal 22 | Aludur 570 |
| | Cobrealtok 17 | 2170 | | MIL-R-5674 | Durcilium | Aldural B | 9002/2 | Alradur |
| | | b17/60 | | QQ-A-225/5 | | Aldural Q | | Orthodur |
| | | Bondur 17/60 | | QQ-A-430 | | | | Avional 25 |
| | | Hedur 1812/48 | | | | | | |
| | | | | | | | | |

EQUIVALENCES 2024 ALUMINIUM-COPPER

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|-------------------|--------|-------------------|----------------|----------------|--------|-----------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlCu4Mg1Si | L-314 | Aludur 580 | CG 42 | QQ-A-200/3 | Duralumin FR | DTD 590 | 24 S | Alradur S |
| | Cobrealtok 24 | Okatur 10 | 24S | QQ-A-225/6 | Carbium dur | DTD 5100 | FD 24 | 6315 |
| | | Heddur 1850/52/57 | | QQ-A-250/4 | Durcilium fort | Aldural G | AV 24 | |
| | | Avional 152 | | QQ-A-430 | | Duralumin G | SD 24 | |
| | | AK2-AK24 | | WW-T-700/3 | | Hiduminium 72 | 9002/4 | |
| | | 2240 | | MII-T-50777 | | Impalco 2024 | | |
| | | Bondur 17/24 | | ASTM B209/210/211 | | 24S | | |
| | | | | ASTM B221/241/316 | | | | |

EQUIVALENCES 3003 ALUMINIUM-MANGANESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|-------------|-------------|--------|-------------------|--------------|----------------|-----------|-----------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlMn1Cu | L-381 | Alforman | MC 10 | QQ-A-220/1 | Alumanganese | Hiduminium 11 | Aluman 30 | Alraman C |
| | Almantok 03 | Mangal | 3S | QQ-A-225/2 | Brial 10 | Impalco 190 | 9003/1 | Aludur 15 |
| | Alucor 11 | Osmagal | D3S | QQ-A-250/2 | | Magalal | 7788 | Aluman |
| | Earman 12 | Heddal 1210 | 31220 | WW-T-700/2 | | 3103 | | ASV2030 |
| | 3S | Venicorr | GM31P | MIL-P-25955 | | | | NA-D3S |
| | | AlMnCu | 5554 | MIL-R-1150 | | | | |
| | | | | MIL-E-15507 | | | | |
| | | | | ASTM B209/210/211 | | | | |
| | | | | ASTM B221/234/241 | | | | |
| | | | | ASTM B345/483/491 | | | | |
| | | | | ASTM B404/313/547 | | | | |
| | | | | ASTM B316 | | | | |
| | | | | SB 209/210/221 | | | | |
| | | | | SB 234/241/247 | | | | |
| | | | | 3003 | | | | |

EQUIVALENCES 3004 ALUMINIUM-MANGANESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|-------------|---------|--------|-------------------|--------|----------------|---------|--------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| | L-382 | (L55) | | SAE 242 | | | 4S | 6511 |
| | Almantok 04 | 3540 | | MG 11A | | | Italox6 | A |
| | | 61/03 | | SB209 | | | 6361 | |
| | | 1224 | | ASTM B209/221/547 | | | 9003/2 | |

EQUIVALENCES 5005A ALUMINIUM-MAGNESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------------|--------|-------------------|---------------|----------------|--------|---------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlMg1 | B57S | Aludur 503 | B57S | ASTM B209/210/483 | Alunox OAL | BA 201 | 5764 | Al1Mg |
| | Earmag 7 | Aludur 100 | | ASTM B316/396/397 | Carbinox 1 | Durcilium | F505 | Aludur 100 |
| | Magnealtok 05 | Peraluman 100 | | | Scleralumag10 | | Pe0,8 | Peraluman 100 |
| | | 510 | | | | | 9005/1 | 4106 |
| | | AM 16 | | | | | | 56571 |
| | | 5010 | | | | | | Alramag 1 |
| | | 63/10 | | | | | | 5583 |
| | | | | | | | | ASV 2084 |
| | | | | | | | | 2586 |

EQUIVALENCES 5019 ALUMINIUM-MAGNESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|-------|--------------|----------|------------|---------------|----------------|--------------|---------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| Al-Mg5 | L-332 | AlMg 5 | GM 50 R | (5056) | A-G 5 | N6 | P-AlMg 5 | Al-5 MG |
| ISO/R 209 | A-G 5 | 3,3555 | CSA HA,6 | ASTM B 211 | NF 57,350 | BS 1470/1/2/3 | UNI 3576 | VSM 10849 |
| ISO/R 826 | 56 S | DIN 1725-45 | GM 50 P | ASTM B 316 | NF 57,650 | BS 1474/5/6/7 | Peraluman 50 | Peraluman 500 |
| ISO/R 828 | | DIN 1746/47 | CSA HA,6 | ER 5356 | Duralinox 5 | Alumagnese 50 | Itallumag 50 | A 56 S |
| | | DIN 1748/49 | 56 S | ASTM B 285 | Carbinox 5 | BA 28 | | |
| | | Aludur 500 | | | Scleralumag 5 | Birmabright 5 | | |
| | | Optal 5 | | | A-G 5 | Hiduminium 05 | | |
| | | Peraluman 50 | | | AIR 9050 B | MG 5 | | |
| | | Supramal 5 | | | AIR 9051 | A 56 S | | |

EQUIVALENCES 5052 ALUMINIUM-MAGNESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------|-----------|--------------------|----------------|----------------|--------------|---------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AIMg2,5 | L-336 | WG-P57S | 57S.52820 | QQ-A-225/7 | Scleralumag 20 | | Itallumag 25 | 17210 |
| | Earmag 25K | 5520 | | QQ-A-250/8 | Carbinox 2 | | FM 24 | 4120 |
| | Magnealtok 25 | 63/52 | | QQ-A-430 | | | Pe 25 | Alramag 25 |
| | | 1528 | | WW-T-700/4 | | | M30 | Peraluman 250 |
| | | | | ASTM B209/210/211 | | | 3574 | Aludur 250 |
| | | | | ASTM B221/241/483 | | | 9005/2 | 4120 |
| | | | | ASTM B404/313/547 | | | | 6526 |
| | | | | ASTM B316 | | | | 2041 |
| | | | | AMS 4016/4017 | | | | 2587 |
| | | | | AMS 4069/4070 | | | | |
| | | | | ASME SB209/210/234 | | | | |
| | | | | ASME SB241 | | | | |

EQUIVALENCES 5083 ALUMINIUM-MAGNESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------------|--------|--------------------|--------|-----------------|--------|---------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AIMg4,5Mn | D54S | Peraluman 460 | D54S | QQ-A-200/4 | 5083 | GB D54S | 7790 | 17215 |
| | Magnealtok 45 | L54 | GM41 | QQ-A-250/6 | | Birmabright BB4 | 9004/5 | (PA44) |
| | Earmag 45M | AM4 | | QQ-A-367 | | BA 281 | | 4140 |
| | | 5510 | | MIL-A-19005 | | Hiduminium-05 | | Alramag 45N |
| | | 61/82 | | MIL-A-46083 | | Peraluman 460 | | Peraluman 460 |
| | | 61/83 | | MIL-A-17358 | | | | Aludur450Mn |
| | | 1542 | | MIL-A-45225 | | | | ASV 2027 |
| | | | | ASTM B209/210/221 | | | | NA-D54S |
| | | | | ASTM B241/345/547 | | | | |
| | | | | ASTM B247 | | | | |
| | | | | AMS 4057/8/9 | | | | |
| | | | | ASME SB209/221/241 | | | | |

EQUIVALENCES 5086 ALUMINIUM-MAGNESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------|--------|-------------------|-------------|----------------|-------------|---------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlMg4 | L-3322/38.341 | 5500 | M57S | QQ-A-200/5 | DuralinoxH4 | | P-AG2M | 424412 |
| | Magnealtok 40 | 63/40 | GM40 | QQ-A-250/7 | Carbinox4 | | 5452 | (17205) |
| | | 1544 | | QQ-A-250/19 | | | Italumag 44 | 1520 |
| | | | | WW-T-700/5 | | | FM 44 | Alramag 4N |
| | | | | MIL-A-21579 | | | Pe44 | Peraluman-410 |
| | | | | MIL-A-19070 | | | 9005/4 | |
| | | | | MIL-T-52234 | | | | |
| | | | | ASTM B209/210/221 | | | | |
| | | | | ASTM B241/345/313 | | | | |
| | | | | ASME SB209 | | | | |
| | | | | ASME SB221 | | | | |
| | | | | ASME SB241 | | | | |

EQUIVALENCES 5154 ALUMINIUM-MAGNESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------|--------|-------------------|--------|-----------------|--------------|------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlMg3,5 | Magnealtok 35 | | C54S | ASTM B209/210/211 | | GB-54S | Itallumag 35 | 2087 |
| | | | GR40 | ASTM B221/547 | | Alcoa 520 | FM3 | Aludur 350 |
| | | | | | | AWCO 27 | Pe 35 | |
| | | | | | | Birmabright BB3 | M35 | |
| | | | | | | BA 27 | 9005/8 | |
| | | | | | | Durcilium -B | | |
| | | | | | | Hiduminium-33 | | |
| | | | | | | Peraluman 460 | | |

EQUIVALENCES 5251 ALUMINIUM-MAGNESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------------|--------|----------|----------------|----------------|---------|-----------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlMg2 | Magnealtok 20 | AlMg2Mn0,3 | M57S | | AG2 | N4 | P-A G2M | 1520 |
| | | WG-M57S | | | Carbinox 2 | | 4511 | 5252 |
| | | Aludur 505 | | | Scleralumag 10 | | | Alramag 2 |
| | | Peraluman 200 | | | | | | 4412 |
| | | (L52) | | | | | | -17205 |
| | | AM26 | | | | | | 424412 |
| | | 3010 | | | | | | |
| | | 63/21 | | | | | | |

EQUIVALENCES 5754 ALUMINIUM-MAGNESIUM

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------------|--------|----------|----------------|----------------|-------|---------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlMg3 | Earmag 25K | WG 53 S | 57S | | AG3 | | | 1530 |
| | Magnealtok 30 | Aludur 507 | | | Duralinox H3 | | | 4113 |
| | | Peraluman 300 | | | Carbinox 3 | | | GA 6533 |
| | | Peraluman 302 | | | Scleralumag 25 | | | PA11N |
| | | 530 | | | | | | Alramag 3 |
| | | AM3 | | | | | | Peraluman 300 |
| | | 5030 | | | | | | MNG 3 |
| | | 63/25 | | | | | | Aludur 300 |
| | | A13 | | | | | | 4130 |
| | | | | | | | | 6533 |
| | | | | | | | | ASV 2014 |

EQUIVALENCES 6005A ALUMINIUM- MAGNESIUM-SILICON

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|------------------|--------|----------|---------|----------------|--------|--------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| | Simalgatok 05 | AlMgSi0,7 3.3210 | | | A-SG0,5 | | 9006/6 | |
| | | Peraluman-062 | | | | | | |
| | | Erbslöh 422 | | | | | | |

EQUIVALENCES 6026 ALUMINIUM-MAGNESIUM-SILICON

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | |
|--|----------|--------|-------------|
| SPAIN | E.E.U.U. | FRANCE | SWITZERLAND |
| 6026 | 6026 | 6026 | 6026 |
| Simalgatok 26 | | | |



EQUIVALENCES 6060 ALUMINIUM-MAGNESIUM-SILICON

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------------|--------|----------|-------------|----------------|--------|--------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlMgSi | Simalgatok 60 | AlMgSi0,5 | G50S | | AGS | H9 | 3569 | 4103 |
| | | Aludur 530 | | | Decoral | | 9006/1 | 6504 |
| | | Aludur 531 | | | Decoral OAL | | | 2080 |
| | | Anticodal-050 | | | Inoxalium | | | 604 |
| | | 460/470 | | | | | | G50S |
| | | AS0,5/AS0,6 | | | | | | 2591 |
| | | 6022 | | | | | | APM046 |
| | | A22,A25 | | | | | | |
| | | 3,3206 | | | | | | |

EQUIVALENCES 6061 ALUMINIUM-MAGNESIUM-SILICON

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|-------------|--------|--------------------|----------|----------------|--------|--------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlMgSiCu | L-3420 38,342 | AS11 | 65S | QQ-A-200/8/16 | (A-GSUC) | GB-65S | 61 s | 1330 |
| | Simagaltok 61 | 6560 | C65S | QQ-A-225/8 | | AWCO-22 | F61 | 2079 |
| | | 19/61 | 69260 | QQ-A-250/11 | | Birmetal-016 | AC 61 | D65S |
| | | 19/62 | 69270 | WW-T-700/6 | | BA 22 | 6170 | |
| | | Pantal 1468 | GS11N | MIL-A-25994 | | Durcilium-Q | 9006/2 | |
| | | | | MIL-A-22771 | | Hiduminium-46 | | |
| | | | | MIL-T-7081C | | L-117 | | |
| | | | | MIL-P-25955 | | L-118 | | |
| | | | | B209/210/211 | | H 20 | | |
| | | | | B221/308/429 | | | | |
| | | | | B241/345/429 | | | | |
| | | | | B483/404/547 | | | | |
| | | | | ASME SB209/210/211 | | | | |
| | | | | ASME SB221/234/241 | | | | |
| | | | | ASME SB247/308 | | | | |

EQUIVALENCES 6063 ALUMINIUM-MAGNESIUM-SILICON

| EQUIVALENTS NATIONAL STANDARDS AND TRADE NAMES | | | | | | | | |
|--|---------------|---------|--------|----------|---------------------|----------------|-------|-----------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlMg0,5Si | L-3441 38,337 | | GS10 | 6063 | QQ-A-200/9 | H9 | 3569 | 4104 |
| | Alucor 46 | | 66050 | | ASTM B210/221/429 | 372B | 63S | A2x5 |
| | Earsimag 11 | | GM41 | | ASTM B241/345/491 | GB-50S | F63 | W1A |
| | 50S | | | | 4156 | Alcoa-910 | AC 63 | Dekoral B |
| | Simagaltok 63 | | | | ASME SB 210/221/241 | AWCO-24 | | 6506 |
| | | | | | | Birmetal-055 | | 173190 |
| | | | | | | BA 24 | | 2055 |
| | | | | | | Durcilium W | | 601 |
| | | | | | | Hiduminium 46 | | C50S |
| | | | | | | Extrudal-050 | | |

EQUIVALENCES 6082 ALUMINIUM-MAGNESIUM-SILICON

| NATIONAL EQUIVALENTS, STANDARDS AND TRADE NAMES | | | | | | | | |
|---|--------|-----------------|--------|----------|----------|-----------------|--------|-----------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlSiMgMn | L-3453 | WG-B51S | B51S | | A-SgM0,7 | H30 | 3571 | 17305 |
| | | Aludur-533 | | | | L15 | RE2 | 4212 |
| | | Antacorodal 110 | | | | GB-51S | 6087 | Dekoral S |
| | | 401/410 | | | | Alcoa 920 | F177 | Antacorodal 112 |
| | | AS1/AS14 | | | | Birmetal 071 | AC11 | S-Korrofestal |
| | | 6010/6012 | | | | BA25 | 9006/4 | 6508 |
| | | 19/20 | | | | Durcilium S | | 2005 |
| | | 19/49 | | | | Hiduminium-44 | | NA-6082 |
| | | A32/A31 | | | | Antacorodal 090 | | 611 |
| | | | | | | | | APM165 |

EQUIVALENCES 6101 ALUMINIUM-MAGNESIUM-SILICON

| NATIONAL EQUIVALENTS, STANDARDS AND TRADE NAMES | | | | | | | | |
|---|--------|--------------------------|--------|-------------------|---------|----------------|---------|------------------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| | L-3431 | 6101 B=E-AlMgSi 3.2305 | D50S | EC QQ-B-825 | Almelec | 91E | 3570 | Rusia: A5E |
| | D50S | 6101C=E-AlMgSi0,5 3.3207 | | WW-C-00540 | E-AGS | D50S | Almelec | E-AlMgSi0,5 |
| | | VAW 19/07 | | ASTM B230/233/262 | A-GS/L | GB-D50S | | Aldrey-051 |
| | | VDM 1400 | | ASTM B317/323/324 | | ALCOA 918 | | E-Aludur 513 |
| | | | | ASTM B373/544 | | AWCO-Silmatec | | 6201 - Anticorodal 041 |
| | | | | | | Durcilium-E | | 6201 -SIS 4102 |
| | | | | | | Hiduminium-47E | | 6201 -Norsk Hydro 612 |
| | | | | | | Aldrey-051 | | Elran 1/-2 |

EQUIVALENCES 7020 ALUMINIUM-ZINC

| NATIONAL EQUIVALENTS, STANDARDS AND TRADE NAMES | | | | | | | | |
|---|---------------|-------------------|--------|----------|-----------------|----------------|--------|------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlZn4,5Mg | Alzintol 20 | AlZn4,5Mg1 | D74S | | A-Z5G | H17 | 7791 | 17410 |
| | L-3741 38,374 | 3,4335 | | | Zicral 3 | | UD 44 | 4425 |
| | | 721,725 | | | Durcilium A-U4N | | Z4 | Perradur |
| | | AZ12 | | | | | 9007/1 | Aludur D2 |
| | | 7350 | | | | | | Unidur-100 |
| | | Constructal 21/51 | | | | | | D 74 S |
| | | Aludur D2 | | | | | | 6950 |
| | | | | | | | | ASV 2596 |

EQUIVALENCES 7075 ALUMINIUM-ZINC

| NATIONAL EQUIVALENTS, STANDARDS AND TRADE NAMES | | | | | | | | |
|---|---------------|-------------------|--------|--------------------|-----------------|----------------|----------|--------------|
| ISO | SPAIN | GERMANY | CANADA | E.E.U.U. | FRANCE | UNITED KINGDOM | ITALY | OTHERS |
| AlZn6MgCu | L-3710 38.271 | AlZnMgCu 1,5 | ZG62 | QQ-A-200/11 | A-Z5GU | 2L95 | 3735 | V95 |
| | Alzintok 75 | 3,4365 | M75S | QQ-A-225/9/12 | Superalumag T50 | L160 | Ergal 55 | Perradur S |
| | | AZ6 | | QQ-A-430 | | | EG55 | Perunal -215 |
| | | Constructal 20/73 | | WW-T-700/7 | | | E51 | Aludur 620 |
| | | Constructal 20/75 | | ASTM B209/210/211 | | | 9007/2 | M75S |
| | | 1750 | | ASTM B221/241/247 | | | | ASV 2082 |
| | | | | ASTM B316 | | | | |
| | | | | AMS 4038/4047/4049 | | | | |
| | | | | AMS 4139/4154/4168 | | | | |
| | | | | ASTM ZG62 A | | | | |

EQUIVALENCES 6012 ALUMINIUM-COPPER

| NATIONAL EQUIVALENTS, STANDARDS AND TRADE NAMES | | | | |
|---|-------------|----------|-------|---------------|
| SPAIN | GERMANY | FRANCE | ITALY | SUIZA |
| L-3452 | AlMgSiPb | A-SGPbBi | 6012 | Anticorodal + |
| | 3,0615 | | | Pb 108 |
| | DIN 1725 | | | |
| | DIN 1746/47 | | | |
| | Autopan | | | |
| | Spanasil | | | |
| | Aludur 533 | | | |
| | Ziertal 58 | | | |

EQUIVALENCES 6262 ALUMINIUM-MAGNESIUM-SILICON (BI+PB)

| COMMERCIAL EQUIVALENT |
|-----------------------|
| ISO |
| AlMg1SiPb |

