

International Equivalences

LEAD-FREE BRASS

EN		DIN		ASTM	BS	JIS	SN
SYMBOLIC	NUMERICAL	SYMBOLIC	NUMERICAL				
CuZn5	CW500L	CuZn5	2.0220	C21000	–	C2100	CuZn5
CuZn10	CW501L	CuZn10	2.0230	C22000	CZ101	C2200	CuZn10
CuZn15	CW502L	CuZn15	2.0240	C23000	CZ102	C2300	CuZn15
CuZn20	CW503L	CuZn20	2.0250	C24000	CZ103	C2400	CuZn20
CuZn28	CW504L	CuZn28	2.0261	–	–	.	CuZn28
CuZn30	CW505L	CuZn30	2.0265	C26000	CZ106	C2600	CuZn30
CuZn33	CW506L	CuZn33	2.0280	C26800	CZ107	C2680	–
CuZn36	CW507L	CuZn36	2.0335	C27000	CZ108	C2700	CuZn36
CuZn37	CW508L	CuZn37	2.0321	C27200	CZ108	C2700	CuZn37
CuZn40	CW509L	CuZn40	2.0360	C28000	CZ109	C2800	CuZn40

LEADED BRASS

EN		DIN		ASTM	BS	JIS	SN
SYMBOLIC	NUMERICAL	SYMBOLIC	NUMERICAL				
CuZn37Pb0,5	CW604N	CuZn37Pb0,5	2.0332	C33500	–	–	CuZn37Pb0,5
CuZn35Pb1	CW600N	CuZn36Pb1,5	2.0331	C34000	CZ118	C3501	CuZn36Pb1
CuZn35Pb2	CW601N	CuZn36Pb1,5	2.0331	C34200	CZ119	–	CuZn35Pb2
				C34500	CZ131		
CuZn37Pb1	CW605N	–	–	C35000	CZ131	C3501	–
CuZn37Pb2	CW606N	–	–	C35300	CZ131	C3601	CuZn37Pb2
CuZn36Pb2As	CW602N	–	–	C35330	CZ132	–	–
CuZn36Pb3	CW603N	2.0375	CuZn36Pb3	C36000	CZ124	C3601	CuZn36Pb3
						C3602	
CuZn38Pb4	CW609N	–	–	–	CZ121/4	C3605	–
CuZn39Pb0,5	CW610N	CuZn39Pb0,5	2.0372	C36500	CZ123	–	CuZn39Pb0,5
CuZn38Pb1	CW607N	–	–	C37000	CZ129	C3501	CuZn38Pb1
CuZn38Pb2	CW608N	–	–	C37700	CZ128	–	CuZn38Pb2
CuZn39Pb2	CW612N	CuZn39Pb2	2.0380	C37700	CZ128	C3771	CuZn39Pb2
CuZn40Pb2	CW617N	CuZn40Pb2	2.0402	C37800	CZ120	C3603	CuZn40Pb2
				C38000		C3604	
CuZn43Pb2Al	CW624N	CuZn44Pb2	2.0410	C38000	–	–	–
CuZn39Pb3	CW614N	CuZn39Pb3	2.0401	C38500	CZ121/3	C3603	CuZn39Pb3
						C3604	

EN		DIN		ASTM	BS	JIS	SN
SYMBOLIC	NUMERICAL	SYMBOLIC	NUMERICAL				
CuZn40Pb1Al	CW616N	–	–	–	–	–	CuZn40Pb1
CuZn42PbAl	CW621N	–	–	–	–	–	–
CuZn39Pb1	CW719R	CuZn38Sn1	3.0530	C46400	CZ133	–	CuZn38Sn1
CuZn31Si	CW708R	CuZn31Si	2.0490	–	–	–	–
CuZn37Mn3Al2PbSi	CW713R	CuZn40Al2	2.0550	C67410	CZ 135	–	CuZn40Al2
CuZn35Ni3Mn2AlPb	CW710R	CuZn35Ni	2.0540	–	–	–	–
CuZn40Mn1Pb1	CW720R	CuZn40Mn1Pb	2.0580	–	CZ136	–	CuZn40Mn1Pb1
CuZn40Mn2Fe1	CW723R	CuZn42Mn2	2.0572	–	–	–	CuZn42Mn2
CuZn20Al2As	CW702R	CuZn20Al2	2.0460	C68700	CZ110	C6870	–