

# International Equivalences

## LEAD-FREE BRASS

EN		DIN		ASTM	BS	JIS	SN
SYMBOLIC	NUMERICAL	SYMBOLIC	NUMERICAL				
CuZn5	CW500L	CuZn5	2.0220	C21000	–	C2100	CuZn5
CuZn10	CW501L	CuZn10	2.0230	C22000	CZ101	C2200	CuZn10
CuZn15	CW502L	CuZn15	2.0240	C23000	CZ102	C2300	CuZn15
CuZn20	CW503L	CuZn20	2.0250	C24000	CZ103	C2400	CuZn20
CuZn28	CW504L	CuZn28	2.0261	–	–	.	CuZn28
CuZn30	CW505L	CuZn30	2.0265	C26000	CZ106	C2600	CuZn30
CuZn33	CW506L	CuZn33	2.0280	C26800	CZ107	C2680	–
CuZn36	CW507L	CuZn36	2.0335	C27000	CZ108	C2700	CuZn36
CuZn37	CW508L	CuZn37	2.0321	C27200	CZ108	C2700	CuZn37
CuZn40	CW509L	CuZn40	2.0360	C28000	CZ109	C2800	CuZn40

## LEADED BRASS

EN		DIN		ASTM	BS	JIS	SN
SYMBOLIC	NUMERICAL	SYMBOLIC	NUMERICAL				
CuZn37Pb0,5	CW604N	CuZn37Pb0,5	2.0332	C33500	–	–	CuZn37Pb0,5
CuZn35Pb1	CW600N	CuZn36Pb1,5	2.0331	C34000	CZ118	C3501	CuZn36Pb1
CuZn35Pb2	CW601N	CuZn36Pb1,5	2.0331	C34200	CZ119	–	CuZn35Pb2
				C34500	CZ131		
CuZn37Pb1	CW605N	–	–	C35000	CZ131	C3501	–
CuZn37Pb2	CW606N	–	–	C35300	CZ131	C3601	CuZn37Pb2
CuZn36Pb2As	CW602N	–	–	C35330	CZ132	–	–
CuZn36Pb3	CW603N	2.0375	CuZn36Pb3	C36000	CZ124	C3601	CuZn36Pb3
						C3602	
CuZn38Pb4	CW609N	–	–	–	CZ121/4	C3605	–
CuZn39Pb0,5	CW610N	CuZn39Pb0,5	2.0372	C36500	CZ123	–	CuZn39Pb0,5
CuZn38Pb1	CW607N	–	–	C37000	CZ129	C3501	CuZn38Pb1
CuZn38Pb2	CW608N	–	–	C37700	CZ128	–	CuZn38Pb2
CuZn39Pb2	CW612N	CuZn39Pb2	2.0380	C37700	CZ128	C3771	CuZn39Pb2
CuZn40Pb2	CW617N	CuZn40Pb2	2.0402	C37800	CZ120	C3603	CuZn40Pb2
				C38000		C3604	
CuZn43Pb2Al	CW624N	CuZn44Pb2	2.0410	C38000	–	–	–
CuZn39Pb3	CW614N	CuZn39Pb3	2.0401	C38500	CZ121/3	C3603	CuZn39Pb3
						C3604	

EN		DIN		ASTM	BS	JIS	SN
SYMBOLIC	NUMERICAL	SYMBOLIC	NUMERICAL				
CuZn40Pb1Al	CW616N	–	–	–	–	–	CuZn40Pb1
CuZn42PbAl	CW621N	–	–	–	–	–	–
CuZn39Pb1	CW719R	CuZn38Sn1	3.0530	C46400	CZ133	–	CuZn38Sn1
CuZn31Si	CW708R	CuZn31Si	2.0490	–	–	–	–
CuZn37Mn3Al2PbSi	CW713R	CuZn40Al2	2.0550	C67410	CZ 135	–	CuZn40Al2
CuZn35Ni3Mn2AlPb	CW710R	CuZn35Ni	2.0540	–	–	–	–
CuZn40Mn1Pb1	CW720R	CuZn40Mn1Pb	2.0580	–	CZ136	–	CuZn40Mn1Pb1
CuZn40Mn2Fe1	CW723R	CuZn42Mn2	2.0572	–	–	–	CuZn42Mn2
CuZn20Al2As	CW702R	CuZn20Al2	2.0460	C68700	CZ110	C6870	–