

## Tolerances

Nominal Diameter		Tolerances of mean diameter		
Above	Up to and inc.	Applicable to the mean diameter	Applicable to any diameter including deviations from the circular shape for straight lengths <sup>ab</sup>	
<b>3</b> °	10	± 0,06	± 0,12	
10	20	± 0,08	± 0,16	
20	30	± 0,12	± 0,24	
30	50	± 0,15	± 0,30	
50	100	± 0,20	± 0,50	
100	200	± 0,50	± 1,00	
200	300 ° The tole	rances indicated in this column are not applicable to:	± 1,50	
300	450	• tubes in rolls or coils • tubes with O色/打孕90 • tubes in an annealed state	± 2,00	

<sup>b</sup> When the diameter is measured at a distance from the ends of the tube of up to 100mm or the equivalent of to a nominal diameter (choosing the lesser of both values), unless otherwise agreed, the tolerance is allowed to be increased by multiplying it by 3.

° Includes 3.

Nominal	exterior diameter	Tolerances of nominal wall thickness t (%)				
mm		t from 0.3 mm up to and inc. 1	t above 1 mm, up to and inc. 3 mm	t above 3 mm, up to and inc. 6 mm	t chove 6 mm up to and inc. 10 mm	t above 10mm
Above	Up to and inc.	mm	t above i mini, up to and inc. 5 mini	t above 5 mm, up to and mc. 6 mm	t above 6 mm, up to and inc. 10 mm	
<b>3</b> ª	40	± 15	± 13	± 11	± 10	-
40	120	± 15	± 13	± 12	± 11	± 10
120	250	_	± 13	± 13	± 12	± 11



Nominal	Nominal exterior diameter Tolerances of nominal wall thickness t (%)					
	mm	t from 0.3 mm up to and inc. 1	t above 1 mm, up to and inc. 3 mm	t above 3 mm, up to and inc. 6 mm	t above 6 mm, up to and inc. 10 mm	t above 10mm
Above	Up to and inc.	mm				
250	450	_	-	± 15	± 15	± 15
	<sup>a</sup> Includes 3.					

## Tolerances of diameter including deviations from circular shape, tubes in rolls or coils

Nominal exterior diameter		Tolerances of nominal diameter including deviations from the circular shape	Applicable to inner diameter of winding	
Above	Up to and inc.		min	
3ª	6	± 0,30	400	
6	10	± 0,50	600	
10	20	± 0,70	800	
20	30	± 0,90	1000	
	<sup>a</sup> Includes 3.			