

Technical characteristics

Designations		Treatment State	Wall Thickness t mm	Tensile Strength R _m N/mm ² min.	Yield Limit at 0.2% Elongation R _{p0.2} N/mm ²		Elongation A %	Hardness				
Material			Up to and including		min.	max		HB		HV		
Symbolic	Numerical											
Cu-DHP	CW024A	M	20	–	–	–	–	–	–	–	–	
		R200 ^a	20	200	–	110	40	–	–	–	–	
		H040 ^a	20	–	–	–	–	40	65	35	60	
		R250	10	250	150	–	20	–	–	–	–	
		H070	10	–	–	–	–	70	100	65	95	
		R290	5	290	250	–	5	–	–	–	–	
		H095	5	–	–	–	–	95	120	90	115	
		–										
		R360	3	360	320	–	–	–	–	–	–	
		H110	3	–	–	–	–	110	–	105	–	

^a In annealed state.