

Bezeichnung		Zustand	Wanddicke t mm máx.	Zugfestigkeit R _m N/mm ² mín.	Dehngrenze 0,2% R _{p0.2} N/mm ²		Bruchdehnung A % mín.	Härte					
Werkstoff					mín.			máx.		HV		HB	
Kurzzeichen	Nummer				mín.	máx.		mín.	máx.	mín.	máx.	mín.	máx.
CuZn40	CW509L	M	20	–	–	–	–	–	–	–	–		
		R340 ^a	20	340	–	250	35	–	–	–	–		
		H075 ^a	20	–	–	–	–	75	105	70	100		
		R410	10	410	250	–	18	–	–	–	–		
		H100	10	–	–	–	–	100	130	95	125		
		R470	5	470	400	–	5	–	–	–	–		
		H125	5	–	–	–	–	125	–	120	–		
^a Geglühter Zustand.													
ANMERKUNG 1 – 1 N/mm ² Einschließlich 1 Mpa.													

KUPFER- ZINK- BLEI LEGIERUNGEN

Bezeichnung		Zustand	Wanddicke t mm máx.	Zugfestigkeit R _m N/mm ² mín.	Dehngrenze 0,2% R _{p0.2} N/mm ²		Bruchdehnung A % mín.	Härte					
Werkstoff					mín.			máx.		HV		HB	
Kurzzeichen	Nummer				mín.	máx.		mín.	máx.	mín.	máx.	mín.	máx.
		M	20	–	–	–	–	–	–	–	–		
		R290 ^a	10	290	–	180	45	–	–	–	–		
		H060 ^a	10	–	–	–	–	60	90	55	85		
CuZn35Pb1	CW600N	R370	10	370	200	–	20	–	–	–	–		
CuZn35Pb2	CW601N	H085	10	–	–	–	–	85	120	80	115		
		R440	5	440	340	–	10	–	–	–	–		
		H115	5	–	–	–	–	115	–	110	–		

Bezeichnung		Zustand	Wanddicke t mm máx.	Zugfestigkeit R _m N/mm ² mín.	Dehngrenze 0,2% R _{p0.2} N/mm ²		Bruchdehnung A % mín.	Härte					
Werkstoff					mín.			máx.		HV		HB	
Kurzzeichen	Nummer				mín.	máx.		mín.	máx.	mín.	máx.	mín.	máx.
CuZn39Pb3 CuZn40Pb2	CW614N CW617N	M	20	–	–	–	–	–	–	–	–		
		R360 ^a	10	360	–	250	25	–	–	–	–		
		H085 ^a	10	–	–	–	–	85	120	80	115		
		R430	10	430	250	–	12	–	–	–	–		
		H115	10	–	–	–	–	115	150	110	145		
		R500	5	500	370	–	8	–	–	–	–		
		H140	5	–	–	–	–	140	–	135	–		
^a Geglühter Zustand.													
ANMERKUNG 1 – 1 N/mm ² Einschließlich 1 Mpa.													

KUPFER – ZINKLEGIERUNGEN KOMPLEX

Bezeichnung		Zustand	Wanddicke t mm máx.	Zugfestigkeit R _m N/mm ² mín.	Dehngrenze 0,2% R _{p0.2} N/mm ² mín.	Bruchdehnung A % mín.	Härte				
Werkstoff							HV		HB		
Kurzzeichen	Nummer						mín.	máx.	mín.	máx.	
CuZn13Al1Ni1Si1	CW700R	M	20	–	–	–	–	–	–	–	
		R380 ^a	10	380	115	50	–	–	–	–	
		H065 ^a	10	–	–	–	65	85	60	80	
		R430	10	430	220	40	–	–	–	–	
		H120	10	–	–	–	120	140	115	135	
		R550	5	550	330	10	–	–	–	–	
		H170	5	–	–	–	170	–	165	–	
		M	20	–	–	–	–	–	–	–	–
CuZn20Al2As	CW702R	R340 ^a	10	340	120	45	–	–	–	–	
		H070a	10	–	–	–	70	100	65	95	
		R390 ^a	5	390	150	40	–	–	–	–	
		H085 ^a	5	–	–	–	85	–	80	–	
		M	20	–	–	–	–	–	–	–	–
		R340 ^a	10	340	120	45	–	–	–	–	

Bezeichnung		Zustand	Wanddicke t mm máx.	Zugfestigkeit R _m N/mm ² mín.	Dehngrenze 0,2% R _{p0.2} N/mm ² mín.	Bruchdehnung A % mín.	Härte			
Werkstoff							HV		HB	
Kurzzeichen	Nummer						mín.	máx.	mín.	máx.
CuZn39Mn1AlPbSi	CW718R	M	20	–	–	–	–	–	–	–
		R440	8	440	200	15	–	–	–	–
		H120	8	–	–	–	120	160	115	155
		R510	8	510	270	10	–	–	–	–
		H145	8	–	–	–	145	–	140	–
CuZn40Mn2Fe1	CW723R	M	20	–	–	–	–	–	–	–
		R440	8	440	170	15	–	–	–	–
		H115	8	–	–	–	115	155	110	150
		R490	8	490	270	10	–	–	–	–
		H135	8	–	–	–	135	–	130	–
^a Geglühter Zustand.										
ANMERKUNG 1 – 1 N/mm ² entspricht 1 Mpa.										